

904-R-605 HMA COARSE AGGREGATE REQUIREMENTS

(Adopted 11-16-12)

The Standard Specifications are revised as follows:

SECTION 904, BEGIN LINE 244, INSERT AS FOLLOWS:

1. HMA Coarse Aggregate

Coarse Aggregate Type	Traffic ESALs		
	< 3,000,000	< 10,000,000	≥ 10,000,000
Air-Cooled Blast Furnace Slag	Yes	Yes	Yes
Steel Furnace Slag	Yes	Yes	Yes
Sandstone	Yes	Yes	Yes
Crushed Dolomite	Yes	Yes	(Note 1)
Polish Resistant Aggregates	Yes	Yes	(Note 1)
Crushed Stone	Yes	No (Note 2)	No (Note 2)
Gravel	Yes	No (Note 2)	No (Note 2)
<p>Note 1. Polish resistant aggregates or crushed dolomite may be used when blended with ACBF or sandstone but cannot exceed 50% of the coarse aggregate by weight (mass), or cannot exceed 40% of the coarse aggregate by weight (mass) when blended with steel furnace slag.</p> <p>Note 2. Crushed stone or gravel in accordance with ITM 221 may be used.</p>			
