

909-R-664 MIXED PAINT PROPERTIES

(Adopted 07-19-17)

The Standard Specifications are revised as follows:

SECTION 909, BEGIN LINE 166, DELETE AND INSERT AS FOLLOWS:

3. Mixed Paint Properties

The mixed paint shall be in accordance with the requirements as follows:

Viscosity, ASTM D 562, Krebs Units 80 - ~~100~~110

SECTION 909, BEGIN LINE 186, DELETE AND INSERT AS FOLLOWS:

pH, ASTM E 707.0 – ~~9.0~~9.5
