414-R-768 ULTRATHIN BONDED WEARING COURSE, WARRANTED

(Revised 10-19-23)

The Standard Specifications are revised as follows:

SECTION 414, BEGIN LINE 19, DELETE AND INSERT AS FOLLOWS:

**Asphalt Materials** 

PG Binder, PG 64-2258S-28, PG 76-2258E-28......902.01(a)

SECTION 414, BEGIN LINE 28, DELETE AND INSERT AS FOLLOWS:

## (b) Asphalt Materials

The PG binder grade shall be selected based on the following requirements:

PG Binder	ESAL
<del>64-22</del> 58S-28	< 10,000,000
<del>76-22</del> 58E-28	$\geq$ 10,000,000

Additional requirements for the PG 76-22 binder as follows:

Characteristic	Test Method	Min.	Max.
Separation, % prepared by ASTM D 7173	AASHTO T 53		<del>6°C</del>
Elastic Recovery, @ 39°F (4°C), %	AASHTO T 301	<del>60</del>	

SECTION 414, BEGIN LINE 97, INSERT AS FOLLOWS:

#### **414.05** Use of Recycled Materials

Recycled materials shall be in accordance with 401.06 for dense graded surfaces, except *RAS shall not be used and* RAP for use in the UBWC mixture shall be 100% passing the 3/8 in. (9.5 mm) sieve and 95 to 100% passing the No. 4 (4.75 mm) sieve.

SECTION 414, BEGIN LINE 159, DELETE AND INSERT AS FOLLOWS:

## 414.10 Pre-Paving Meeting

A pre-paving meeting between the Engineer and Contractor will be held on-site prior to beginning work. The following shall be reviewed:

- (a) work schedule
- (b) traffic control plan
- (c) equipment calibrations and adjustments
- (d) inspection and evaluation of the condition and adequacy of equipment, including units for transport of materials
- (e) <del>JMF</del>DMF
- (f) Contractor's proposed emulsion and mix application rates
- (g) QCP in accordance with ITM 803
- (h) Contractor's authorized representative.

SECTION 414, BEGIN LINE 198, DELETE AND INSERT AS FOLLOWS:

The Contractor shall furnish to the Engineer a warranty bond at the pre-construction conference or prior to beginning any work on the contract. The warranty bond shall be equal to 100% of the contract total for the warranted UBWC pay items, and shall be

properly executed by a surety satisfactory to the Department, and shall be payable to the State of Indiana. The warranty bond shall be in effect for threeone years from the date of substantial completion.

SECTION 902, BEGIN LINE 81, DELETE AND INSERT AS FOLLOWS:

# 2. Asphalt Emulsion Ultrathin Bonded Wearing Course

Characteristics		Test Method	Min.	Max.
Viscosity, Saybolt Furol @ 25°C (77°F-(25°C), s		AASHTO T 59	20	100
Storage Stability Test, 24 h, % (Note 1)		AASHTO T 59		1
Sieve Test, %		AASHTO T 59		0.05
Residue by Distillation, % (Note 21)		AASHTO T 59	63	
Oil Distillate by volume of emulsified asphalt, %		AASHTO T 59		2
Demulsibility, %	w/35 mL, 0.02 N CaCl2 or	AASHTO T 59	60	
	w/35 mL, 0.8% DSS	AASHTO T 59		
	Tests on Residue from Di	stillation		
Penetration (0.1 mm) at 77°F (25°C), 100g, 5 s		AASHTO T 49	90	150
Elastic Recovery @ 4°C (39°F-(4°C), %		AASHTO T 301	58	
3.7		•		•

#### Notes:

<sup>1.</sup> After 24 h, the emulsion shall be a homogeneous colorThe distillation temperature for this test shall be 175°C (350°F).

<sup>2.</sup> Except maximum temperature of  $400 \pm 10^{\circ}F$  ( $205 \pm 5^{\circ}C$ ).