

DIVISION 500 – CONCRETE PAVEMENT

SECTION 501 – QC/QA PORTLAND CEMENT CONCRETE PAVEMENT, PCCP

501.01 Description

This work shall consist of QC/QA portland cement concrete pavement, PCCP, placed on a prepared subgrade or subbase in accordance with 105.03.

501.02 Quality Control

10 The mixture for PCCP shall be produced by an approved plant in accordance with ITM 405, transported, and placed according to a Quality Control Plan, QCP, prepared and submitted by the Contractor in accordance with ITM 803, for PCCP. The QCP shall be submitted to the Engineer at least 15 days prior to commencing PCCP paving operations.

An American Concrete Institute certified concrete field testing technician, grade I, shall be on site to direct all sampling and testing.

A common testing facility shall be provided for both production control and acceptance testing.

20

MATERIALS

501.03 Materials

Materials shall be in accordance with the following:

	Admixtures	912.03
	Coarse Aggregate, Class AP, Size No. 8*	904
	Fine Aggregate, Size No. 23*	904
	Fly Ash	901.02
30	Ground Granulated Blast Furnace Slag	901.03
	Portland Cement	901.01(b)
	Rapid Setting Patch Materials	901.07
	Water	913.01

* Or gradation as identified in the QCP

501.04 Concrete Mix Design

40 A concrete mix design submittal, CMDS, shall be in accordance with 501.05. The CMDS shall be submitted to and approved by the DTE. The CMDS shall be submitted a minimum of seven calendar days prior to the trial batch utilizing the Department provided spreadsheet and shall include the following:

- (a) a list of all ingredients
- (b) the source of all materials
- (c) the fine to total aggregate ratio

501.04

- (d) the gradation of the aggregates
- (e) the absorption of the aggregates
- (f) the SSD bulk specific gravity of the aggregates
- (g) the specific gravity of pozzolan
- (h) the batch weights
- 50 (i) the names of all admixtures
- (j) the admixture dosage rates and the manufacturer's recommended range.

The CMDS is used to conduct a trial batch in accordance with 501.06. Upon completion of the trial batch, the Contractor shall submit the concrete mix design for production, CMDP. The CMDP shall be submitted to the DTE utilizing the Department furnished spreadsheet a minimum of three work days prior to production. Production shall not commence without an approved CMDP. Both the Contractor's and the Engineer's test results from the trial batch will be included in the CMDP submittal.

60

A CMDP may be changed or adjusted in accordance with the following:

(a) Change in Materials

A change in a previously approved CMDP, for a given contract, to any of the following shall be submitted to the DTE as a CMDS, referencing the original CMDP.

- 1. cement source or type
- 2. pozzolan source or type
- 70 3. coarse aggregate source or type
- 4. admixture type.

A trial batch shall be conducted in accordance with 501.06, or verification of the new CMDS may be made during the first day of production by tests conducted by the Contractor and the Engineer. Acceptance test results may be used for the Engineer's verification tests. Production may continue until flexural strength tests are completed, provided all other properties are in accordance with 501.06. The test results shall be submitted to the DTE utilizing the Department spreadsheet no later than one day after the flexural strength test results are complete. If the flexural strength is not in accordance with 501.06, production shall stop and all PCCP constructed with the new CMDS will be adjudicated as a failed material in accordance with normal Department practice as listed in 105.03.

80

(b) Adjustments to Materials

An adjustment in a previously approved CMDP, for a given contract, to any of the following shall be submitted to the DTE as a CMDS, referencing the original CMDP.

- 1. admixture source
- 90 2. admixture product of the same type and from the same source designated in the original CMDP

- 3. fine aggregate source
- 4. target unit weight due to change in aggregate properties
- 5. fine to total aggregate ratio in excess of $\pm 3\%$ from the value designated by the original CMDP
- 6. increase in cement content from the amount designated in the original CMDP.

100 The new CMDS shall be submitted to the DTE utilizing the Department spreadsheet a minimum of one work day prior to production. A trial batch or verification testing is not required for approval. Production shall not commence without an approved CMDP.

(c) Other Adjustments

Other adjustments in an approved CMDP, for a given contract, to any of the following will be allowed and DTE notification and approval prior to use is not required.

- 110 1. admixture dosage rate
- 2. fine aggregate to total aggregate ratio within $\pm 3\%$ of the value designated by the original CMDP.

An approved CMDP from a previous contract may be used on additional contracts. The CMDP shall be submitted to the DTE for review and approval prior to use.

501.05 Concrete Mix Criteria

The CMD shall produce workable concrete mixtures having the following properties:

120

Minimum portland cement content.....	400 lbs/cu yd
Maximum water/cementitious ratio.....	0.450
Minimum portland cement/fly ash ratio	3.2 by weight
Minimum portland cement/GGBFS ratio	2.3 by weight
Target air content.....	6.5%
Minimum flexural strength, third point loading	570 psi at 7 days

130 The Contractor may elect to use fine and coarse aggregates in accordance with 904, or may propose the use of alternate gradations. If alternate gradations are proposed, the QCP shall specify the tolerances of material passing each sieve. In either case, 100% of the coarse aggregate shall pass the 1 in. (25 mm) sieve. The combined amount of fine and coarse aggregates passing the No. 200 (75 μ m) sieve shall be from 0% to 2.0% for fine aggregate and gravel, and from 0% to 2.5% for fine aggregate and crushed stone or crushed slag.

The fine aggregate shall be at least 35% but not more than 50% of the total weight of the aggregate in each cubic yard. Proportions will be based upon saturated surface dry aggregates.

140 Absorption tests shall be performed on the fine aggregate in accordance with AASHTO T 84 and on the coarse aggregate in accordance with AASHTO T 85. Absorption test results for a particular size of aggregate that differ by more than 1.0 percentage point from the Department's source value shall be investigated. The Contractor shall report any differences that exceed 1.0% to the Department. The Contractor's results shall be used when calculating the water/cementitious ratio.

150 Fly ash or GGBFS used as an additive, or blended cements may only be incorporated in the concrete mix between April 1 and October 15 of the same calendar year. If type IP, type IP-A, type IS or type IS-A cements are to be used, the minimum portland cement content shall be increased to 500 lbs/cu yd. The use of fly ash or GGBFS as an additive will not be allowed when blended cement types IP, IP-A, IS, or IS-A are used.

Water reducing admixture type A, or water reducing and retarding admixture type D, may be used in PCCP. However, admixture type A shall not be used in conjunction with admixture type D.

501.06 Trial Batch

160 A trial batch shall be produced and tested by the Contractor's certified technician to verify that the CMDS meets the concrete mix criteria. Concrete produced at a plant shall be batched within the proportioning tolerances of 508.02(b). Concrete batched in a laboratory shall be in accordance with ASTM C 192. The Engineer will test the trial batch and provide the Contractor with the results. The trial batch shall be of sufficient quantity to allow the Contractor and the Engineer to perform all required tests from the same batch. Trial batch concrete shall not be used for more than one test, except the concrete used for the unit weight may be used to conduct the air content test. The air content shall be 5.0% to 10.0%. The plastic unit weight shall be within $\pm 3.0\%$ from the target plastic unit weight of the CMDS. The water/cementitious ratio shall be within ± 0.030 of the target value of the CMDS and shall not exceed 0.450. The flexural strength shall be determined by averaging a minimum of two beam breaks and shall be a minimum of 570 psi.

170

Test results shall be added to the Department spreadsheet and submitted to the DTE in accordance with 501.04. Adjustments to the target unit weight and the target water/cementitious ratio may be made.

A trial batch is not required for a CMDS that has any of the following criteria:

- 180
- (a) minimum cement content of 564 lbs/cu yd and a target water/cementitious ratio of 0.420
 - (b) class C concrete in accordance with 702 using Class AP coarse aggregate.

501.07 Lots and Sublots

Lots will be defined as 7,200 sq yd of PCCP. Lots will be further subdivided into sublots of 2,400 sq yd of PCCP within a lot. Partial sublots of 480 sq yd or less will be added to the previous subplot. Partial sublots greater than 480 sq yd constitute a full subplot. Partial lots of one or two sublots constitute a full lot.

190

Lots and sublots will be numbered and tested for a given pay item regardless of the number of CMD's used and will be closed out at the end of the paving season or construction phase.

501.08 Acceptance

Acceptance of PCCP for flexural strength, air content, unit weight, water/cementitious ratio, and thickness will be determined on the basis of tests performed by the Engineer in accordance with 505. The Engineer will randomly select the location within each subplot for sampling in accordance with ITM 802.

200

The random sample per subplot shall be of sufficient quantity to perform all required tests and obtained in accordance with AASHTO R 60. Concrete and necessary labor for sampling shall be furnished as required by the Engineer. The test results of the sublots for each lot will be averaged and shall be in accordance with 501.05 and 501.06, except the lot average for thickness shall be in accordance with 501.26. Test results are to be shared in a timely manner.

Test or Determination	Frequency	Test Method	Precision
7-Day Flexural Strength	two beams per subplot	AASHTO T 97	1 psi
Air Content	one per subplot	AASHTO T 152 or ASTM C 173	0.1
Unit Weight	one per subplot	AASHTO T 121	1
Water/Cementitious Ratio	one per two lots	ITM 403	0.001
Thickness	two per subplot	ITM 404	0.1

Rounding will be in accordance with 109.01(a).

210

In the event that an acceptance sample is not available to represent a subplot, all test results of the previous subplot will be used for acceptance. If the previous subplot is not available, the subsequent subplot will be used for acceptance.

CONSTRUCTION REQUIREMENTS**501.09 General**

Equipment for PCCP shall be in accordance with 508.

220

501.10 Preparation of Grade

The subgrade shall be shaped to the required grade and section, free from all ruts, corrugations, or other irregularities, and uniformly compacted and approved in accordance with 207.

501.11 Preparation of Subbase

Subbase, if required, shall be placed and shaped to the required grade and section in accordance with 302. Construction traffic shall not be allowed on the aggregate drainage layer of the subbase, except where PCCP placement is restricted. Exceptions shall be submitted for approval.

230

501.12 Placement

Placement of PCCP shall be by the slipformed or formed methods with equipment specified in 508.04. The subgrade or subbase shall be uniformly moist at the time of PCCP placement. Excessively dry subgrade or subbase shall be sprinkled with water.

501.13 Process Control

The Engineer and the Contractor will jointly review the operations to ensure compliance with the QCP. Continuous violations of compliance with the QCP will result in suspension of paving operations.

240

501.14 Concrete Mixing and Transportation

Concrete shall be mixed and delivered by one of the following:

- (a) Central mixed concrete shall be completely mixed in a stationary mixer and transported in a truck agitator, truck mixer at agitating speed, or non-agitating equipment.
- (b) Shrink mixed concrete shall be partially mixed in a stationary mixer and the mixing completed during transportation in a truck mixer.
- (c) Transit mixed concrete shall be completely mixed in a truck mixer.

250

The batch ticket for contract dedicated plants and delivery tickets for ready mix plants shall include the approved CMDP number. The tickets shall be delivered to the Engineer.

260

When the concrete temperature is 90°F or above, discharge from non-agitating equipment shall be completed within 30 minutes of mixing the water, cement, and aggregates. For concrete temperature below 90°F, discharge from non-agitating equipment shall be completed within 45 minutes of mixing the water, cement, and aggregates. The concrete temperature shall be measured in accordance with ASTM C 1064 at the point of delivery.

A watertight cover shall be used for a truck agitator and non-agitating equipment. The concrete shall be incorporated into the paving equipment within 15 minutes of discharge by the truck mixer, truck agitator, or non-agitating equipment.

270 Discharge from a truck agitator or a truck mixer shall be completed within 90 minutes of mixing the water, cement, and aggregates.

Concrete shall be uniformly mixed when delivered to the job site. The Engineer may conduct additional testing to verify uniformity of the mixture. Additional testing will consist of slump tests taken in accordance with AASHTO T 119 at approximately the 1/4 and 3/4 points of a load. If the slumps differ by more than 1 in. when the average slump is 3 in. or less, or by more than 2 in. when the average slump is greater than 3 in., paving operations may be suspended while the mixing process is jointly reviewed and problems resolved by the Engineer and the Contractor.

280

Wash water shall not be used as a portion of the mixing water.

When concrete is delivered in transit mixers, additional water to increase the workability of a load may be added within 45 minutes of initial mixing per the QCP. Any addition of water shall be noted on the batch ticket and shall not occur as a continuing operation.

501.15 Weather Limitations

290 PCCP shall not be placed on frozen subgrade or subbase. PCCP shall be placed when the ambient temperature is 35°F and above, unless procedures outlined in the QCP for lower temperatures are followed. Prior to attaining opening to traffic strengths in accordance with 501.23, sufficient means shall be taken to prevent the PCCP from freezing.

501.16 Placing Concrete

The batches shall be deposited so as to have a uniform mix and require as little rehandling as possible. The plastic concrete shall not be segregated during placement. Dowel bars and assemblies shall not be displaced during placement of concrete.

300

Concrete shall be thoroughly consolidated against the faces of all forms or adjacent concrete surfaces. Hand placed concrete shall be thoroughly consolidated with the use of a vibrator. Vibrators shall not operate in any one location so as to bring excessive mortar to the surface, and shall not come in contact with a dowel bar assembly, subgrade, subbase, or forms.

Concrete shall be placed around manholes or similar structures in accordance with 720.

310

The Contractor shall be responsible for the protection of the existing joints from the intrusion of fresh concrete mortar, and for any damage to existing pavement caused by the operation of mechanical equipment. Concrete materials that fall on or are worked into the joints or surface tines of an existing slab, shall be removed immediately.

Concrete shall not be mixed, placed, or finished when the natural light is insufficient, unless an adequate and approved artificial lighting system is operated in

501.17

accordance with the QCP.

320 The Contractor shall have available at all times sufficient materials for the protection of unhardened PCCP from the effects of rain. Covering material such as burlap or polyethylene sheeting shall be provided. When rain appears imminent, paving operations shall stop. All available personnel shall be used to cover the PCCP.

501.17 Blank

501.18 Joints

Joints shall be in accordance with 503.

501.19 Finishing

330 PCCP shall be finished in accordance with 504.

501.20 Curing

PCCP shall be cured with an approved white pigmented liquid membrane forming compound. Alternative methods of curing may be approved by the Engineer. Curing shall be in accordance with 504. For formed PCCP, immediately after the forms are removed, the sides of the PCCP shall be cured.

501.21 Form Removal

340 Forms may be removed as soon as the PCCP has hardened sufficiently to prevent edge spalling or other damage. Form pullers shall not be supported on the PCCP during form removal operations.

501.22 Pavement Inspection

The Contractor and the Engineer will conduct an inspection of the new PCCP for any damage, including freezing or random cracks. The inspection and all necessary repairs shall be completed prior to opening the pavement to non-construction traffic. All random, full-depth cracks in the PCCP shall be corrected in accordance with 503.06. All other damage shall be repaired by approved methods.

350 **501.23 Opening to Traffic**

The Contractor shall be responsible for controlling the opening of the PCCP to construction and non-construction traffic and include the procedures in the QCP. Pavement inspection will be completed in accordance with 501.22.

(a) Construction

360 Construction vehicles or equipment will be allowed on the PCCP after 10 days or when flexural tests indicate a modulus of rupture of 550 psi or greater. ITM 402 may be used as an alternate method to determine the flexural strength. All construction vehicles or equipment that may damage the PCCP shall not be used on the PCCP unless adequate protection is provided. Approved joint cutting saws may be operated on the PCCP.

(b) Non-Construction

370 PCCP may be opened to traffic after 14 days. The PCCP may be opened earlier if test beams or ITM 402 indicate a modulus of rupture of 550 psi or greater. If adequate strengths are not met within 14 days, an investigation by the Engineer and the Contractor will be conducted to determine if the PCCP is deficient. Resolutions for all deficiencies will be developed at the completion of the investigation. Cracks and joints shall be sealed in accordance with 503.05 and the PCCP cleaned prior to opening to traffic.

501.24 Pavement Corrugations

Pavement corrugations shall be in accordance with 606.

501.25 Pavement Smoothness

Pavement smoothness will be accepted by means of a profilograph, a 16 ft long straightedge, or a 10 ft long straightedge as described below.

(a) Profilograph

380 When a pay item for Profilograph, PCCP is included in the contract, the Contractor shall furnish, calibrate, and operate an approved profilograph in accordance with ITM 912 for the acceptance of longitudinal smoothness on the mainline traveled way and ramps, including adjacent acceleration or deceleration lanes, where both of the following conditions are met:

1. The design speed is greater than 45 mph.
2. The traveled way or ramp lane width is constant and is 0.1 mi in length or longer.

390

The profilogram produced shall become the property of the Department. The profilograph shall remain the property of the Contractor.

The project area, less paving exceptions and areas exempt from profilograph operation in accordance with ITM 912, will be divided into individual smoothness sections measuring 0.1 mi in length for each lane. Partial length smoothness sections adjacent to project limits, paving exceptions, or areas exempt from profilograph operation will be considered in accordance with ITM 912.

400

If the posted speed limit for an entire smoothness section is less than or equal to 45 mph, the section will be exempt from profilograph operation and the smoothness within the section will be accepted by a 16 ft straightedge.

If the posted speed limit is greater than 45 mph for a portion of a smoothness section and is less than or equal to 45 mph for the remainder, the section smoothness acceptance will be as follows:

- 410
1. By profilograph for the portion of the section with a posted speed limit greater than 45 mph.
 2. By 16 ft straightedge for the portion of the section with a posted speed limit less than or equal to 45 mph.

At locations where the profilograph is required, all high or low point deviations which are greater than 0.30 in. shall be corrected. Corrections shall be made in accordance with 501.25(c).

(b) 16 ft Straightedge and 10 ft Straightedge

420 The Department will furnish and operate 16 ft and 10 ft straightedges as described below. The 16 ft straightedge is used to accept smoothness along the direction of mainline traffic and the 10 ft straightedge is used to accept smoothness transverse to the direction of mainline traffic. This includes longitudinal smoothness on public road approaches and median crossovers.

For contracts which include the profilograph, PCCP pay item, the 16 ft long straightedge will be used to accept longitudinal smoothness at the following locations:

- 430
1. All mainline traveled way lanes shorter than 0.1 mi.
 2. All mainline traveled way lanes within smoothness sections with posted speed limits less than or equal to 45 mph throughout the entire section length.
 3. All mainline traveled way lanes at locations exempted from profilograph operation in accordance with ITM 912.
 4. All tapers.
 - 440 5. All turn lanes, including bi-directional left turn lanes.
 6. All ramps with design speeds of 45 mph or less.
 7. All acceleration and deceleration lanes associated with ramps with design speeds of 45 mph or less.
 8. All shoulders.

450 For contracts where the profilograph is not used for smoothness acceptance, the 16 ft straightedge will be used to accept longitudinal smoothness at the above locations and on all mainline traveled way lanes and ramps with design speeds greater than 45 mph. Smoothness acceptance on ramp acceleration or deceleration lanes will also be accepted by the 16 ft straightedge.

The 10 ft long straightedge shall be used for transverse slopes, approaches, and crossovers.

As soon as the PCCP has cured sufficiently, the smoothness may be checked. The Department may direct that the pavement profile be evaluated within 24 h following placement. When profile testing is consistently outside pavement surface tolerances the paving operation shall be discontinued until an amended QCP is submitted.

(c) Smoothness Correction

Pavement smoothness variations outside specified tolerances shall be corrected by grinding with a groove type cutter or by replacement. Grinding will not be allowed until the PCCP is 10 days old or the flexural strength test is 550 psi or greater. The grinding of the pavement to correct the profile shall be accomplished in either the longitudinal or the transverse direction. The PCCP texture after grinding shall be uniform. If the grinding operation reduces the tining grooves to a depth of less than 1/16 in. and the longitudinal length of the removal area exceeds 15 ft, or two or more areas are within 30 ft of each other, the PCCP shall be re-textured in accordance with 504.03.

At locations where the profilograph is used, all areas having a high or low point deviation in excess of 0.30 in. shall be corrected. In addition, smoothness sections with a deficient profile index in accordance with 501.28(d) shall be corrected. After the corrective action is complete, the profilograph shall be operated throughout the entire affected smoothness section to verify the adequacy of the corrective action.

At locations where the 16 ft straightedge is used, the pavement variations shall be corrected to 1/4 in. or less. At locations where the 10 ft straightedge is used, the pavement variations shall be corrected to 1/8 in. or less.

501.26 Pavement Thickness

PCCP thickness shall be determined after all corrective grinding. The Contractor shall obtain cores at the locations determined by the Engineer in accordance with ITM 802. Cores, 4 in. in diameter, shall be taken in the presence of the Engineer for the full depth of the PCCP. The Engineer will take immediate possession of the cores. Cores shall not be taken within 6 in. of the edge of pavement, within 3 in. of longitudinal joints, within 2 ft of D-1 contraction joints, or within 5 ft of a transverse construction joint. Cores shall be taken and measured in accordance with ITM 404. All core holes shall be filled with PCC or rapid setting patch material within 24 h of drilling.

The width of adjudicated PCCP shall be the width of pavement lane in which the deficiency occurs. Pavement that has been replaced shall be investigated for thickness.

The thickness of the PCCP for each subplot shall be the average lengths of both cores from the subplot. Calculations shall be to the nearest 0.1 in.

500 **501.27 Tolerance**

Plastic unit weight, water/cementitious ratio, flexural beam, and air content tests will be performed during PCCP operations.

(a) Plastic Unit Weight

Sublots shall not vary by more than $\pm 3.0\%$ from the target unit weight. A stop paving order will be issued if the plastic unit weight exceeds $\pm 3.0\%$ from the target plastic unit weight. Paving operations shall not resume until satisfactory changes are made or an alternate CMDP is used.

510 Calculations for the plastic unit in lbs/cu yd will be made and reported to the nearest figure in the tenth.

(b) Water to Cementitious Ratio

The weekly water to total cementitious materials ratio shall not vary more than ± 0.030 of the target value or exceed 0.450. A stop paving order will be issued if the test results exceed these values. Paving operations shall not resume until satisfactory changes are made or an alternate CMDP is used.

520 Calculations for water to cementitious ratio will be made and reported to the nearest figure in the third decimal place.

(c) Flexural Strength

Average lot values of 570 psi and above shall be achieved. Price adjustments for values outside the tolerance limits will be in accordance with 501.28.

Calculations for flexural strength in psi will be made and reported to the nearest whole unit.

(d) Air Content

530 The average lot air content values shall not vary more than - 0.8% to + 2.4% from the 6.5% target air content. The range of sublot air content values shall not exceed 2.5%. Price adjustments for values outside the tolerance limits or range will be in accordance with 501.28.

Calculations for air content percentage will be made and reported to the nearest figure in the first decimal place.

501.28 Pay Factors

540 When the PCCP test results for flexural strength, air content, air content range, smoothness, and thickness exceed the allowable tolerances, pay factors will be determined. The pay factors will be used to calculate a quality assurance adjustment quantity for the lot.

The adjustment for flexural strength, air content, air content range, thickness, and smoothness will be calculated as follows:

$$q = L \times U \times (P - 1.00)$$

where:

q = quality assurance adjustment quantity
 L = lot quantity
 U = unit price for QC/QA-PCCP, \$/sq yd
 P = pay factor.

550

For subplot thickness determination:

$$q_T = I_T \times U \times (P - 1.00)$$

where:

q_T = quality assurance adjustment quantity
 I_T = subplot quantity for thickness
 U = unit price for QC/QA-PCCP, \$/sq yd
 P = pay factor.

The quality assurance adjustment points for smoothness, Q_s , will be calculated in accordance with 501.28(d).

560

The total quality assurance adjustments will be calculated as follows:

$$Q_T = \Sigma (q_{T1} + q_{T2} + q_{T3}), \text{ and}$$

$$Q = \Sigma (q_F + q_A + q_R + Q_T) + Q_s$$

where:

Q = total quality assurance adjustment quantity
 Q_s = quality assurance adjustment for smoothness
 q_F = lot quality assurance adjustments for flexural strength
 Q_T = lot quality assurance adjustments for thickness
 q_A = lot quality assurance adjustments for air content
 q_R = lot quality assurance adjustments for range.

570

If the Contractor is not required to remove the pavement or take other corrective actions, quality assurance adjustments of the lot will be assessed as determined by the Office of Materials Management.

(a) Flexural Strength

When test results for flexural strength exceed the allowable tolerance, a pay factor will be assessed as follows:

1. Lots

Lot Average Flexural Strength	
Psi	Pay Factors
570 and above	1.00
565 – 569	0.98
560 – 564	0.96
555 – 559	0.94
550 – 554	0.92
545 – 549	0.89
540 – 544	0.86
535 – 539	0.83
525 – 534	0.78
515 – 524	0.72
514 or less	*
* The PCCP will be adjudicated as a failed material in accordance with normal Department practice as listed in 105.03. The PCCP may be subject to removal and replacement or left in place with reduced or no payment.	

2. Sublots

580 If a subplot value is less than 500 psi, the PCCP will be adjudicated as a failed material in accordance with normal Department practice as listed in 105.03. For a subplot completely removed, the subplot test value from the replacement subplot will replace the original test value.

(b) Air Content

When test results for air content exceed the allowable tolerance or range, a pay factor will be assessed as follows:

1. Lots

Lot Average Air Content	
Percent, %	Pay Factors
> 9.8	*
9.7 – 9.8	0.80
9.5 – 9.6	0.90
9.3 – 9.4	0.95
9.0 – 9.2	0.99
5.7 – 8.9	1.00
5.6	0.93
5.5	0.90
5.4	0.85
5.3	0.79
< 5.3	*
* The PCCP will be adjudicated as a failed material in accordance with normal Department practice as listed in 105.03. The PCCP may be subject to removal and replacement or left in place with reduced or no payment.	

Lot Range for Air Content	
Percent, %	Pay Factors
0.0 – 2.5	1.00
2.6 – 3.0	0.99
3.1 – 3.5	0.97
> 3.5	*
* The PCCP will be adjudicated as a failed material in accordance with normal Department practice as listed in 105.03. The PCCP may be subject to removal and replacement or left in place with reduced or no payment.	

590

2. Sublots

If a subplot value is less than 5.0% or greater than 10.0%, the PCCP will be adjudicated as a failed material in accordance with normal Department practice in accordance with 105.03. For a subplot completely removed, the subplot test value from the replacement subplot will replace the original test value.

(c) Thickness

When test results for pavement thickness do not meet the specified thickness, a pay factor will be assessed as follows:

600

Sublot Pay Factors for Thickness	
Average core depth, ACD Design depth, DD	
ACD minus DD	Pay Factor
> +0.5 in.	1.05
+0.3 in. to +0.5 in.	1.02
±0.2 in.	1.00
-0.3 in. to -0.5 in.	0.96
-0.6 in. to -0.7 in.	0.90
-0.8 in. to -1.0 in.	0.80
< -1.00 in.	*
* The PCCP will be adjudicated as a failed material in accordance with normal Department practice as listed in 105.03. The PCCP may be subject to removal and replacement or left in place with reduced or no payment.	

(d) Smoothness

When the pavement smoothness is tested with a profilograph, pavement will be based on a zero blanking band on the final profile index. A Quality Assurance Pay Factor, PFs, for smoothness will apply to the planned thickness of the PCCP. The quality assurance adjustment for each section will include the total area of each pavement lane measured by the profilograph for 0.1 mi long section represented by the profile index calculated by the following formula:

610

$$q_s = (PF_s - 1.00) \times A \times U$$

where:

- q_s = quality assurance adjustment for smoothness for one section
- PF_s = pay factor for smoothness
- A = area of the section, sq yd
- U = unit price for the material \$/sq yd.

For smoothness sections that are less than 0.1 mi in length or require profilograph operation along both lane edges, the profile index used to obtain the smoothness pay factor used in the above formula will be determined in accordance with ITM 912.

620 The quality assurance adjustment for smoothness, Q_s , for the contract will be the total of the quality assurance adjustments for smoothness, q_s , on each section by the following formula:

$$Q_s = \sum q_s$$

Regardless of the tabulated value, the maximum pay factor for a smoothness section where corrective action has been performed will be 1.00.

Pay Factors for Smoothness ($PI_{0.0}$) Zero Blanking Band	
Design Speed greater than 45 mph	
Profile Index, in./0.1 mi.	Pay Factor, PF_s
over 0.00 to 1.40	1.06
over 1.40 to 1.60	1.05
over 1.60 to 1.80	1.04
over 1.80 to 2.00	1.03
over 2.00 to 2.40	1.02
over 2.40 to 2.80	1.01
over 2.80 to 3.60	1.00
over 3.60 to 3.80	0.96
All pavements with a Profile Index, $PI_{0.0}$, greater than 3.80 in. shall be corrected to a profile index less than or equal to 3.80 in.	

501.29 Appeals

630 If the Contractor does not agree with the acceptance test results, a request may be made in writing for additional tests for a subplot or lot. The basis of the appeal shall include applicable QC test results showing acceptable quality results and shall be submitted within five calendar days of receipt of the Department’s written results for that lot. Upon review of the appeal, the Engineer may accept the PCCP in accordance with 105.03 or accept the appeal.

(a) Flexural Strength

640 Appeals will not be considered unless QC test results indicate greater than a 50 psi difference between the Department’s and the Contractor’s tests. Upon approval for the additional testing, the Contractor shall obtain cores, as directed, in the presence of the Engineer.

The Engineer will determine the location of the cores within the appealed and adjacent sublots using the same CMD. The location of the cores will be at the center of a lane at the acceptance sample location. Cores shall not be taken over dowels or within 5 ft of a header. Two cores shall be taken in each subplot for the full depth of pavement and shall be 4 in. in diameter. All core holes shall be filled with portland cement concrete within 24 h of drilling. If adjacent sublots were produced using different CMDs, the matter will be adjudicated as a failed material in accordance with normal Department practice.

650

Each core will be tested for split tensile strength in accordance with ASTM C 496. The cores will be submerged in lime saturated water prior to testing for a minimum of 40 h.

The average core split tensile strength will be determined for the appealed and adjacent sublots. Flexural strength will be calculated as follows:

$$F_D = S_D \times \left[\frac{F_{A1}}{2S_{A1}} + \frac{F_{A2}}{2S_{A2}} \right]$$

660 where:

- F_D = flexural strength of the appealed subplot
- F_{A1} = flexural strength of the previous adjacent subplot
- F_{A2} = flexural strength of the subsequent adjacent subplot
- S_D = split tensile strength of the appealed subplot
- S_{A1} = split tensile strength of the previous adjacent subplot
- S_{A2} = split tensile strength of the subsequent adjacent subplot.

(b) Air Content

Appeals will not be considered unless QC test results indicate greater than a 0.5% difference between the Department's and the Contractor's tests. Upon approval for the additional testing, the Contractor shall obtain core as directed in the presence of the Engineer.

670

The Engineer will determine the location of the core within the appealed subplot. The location of the core will be at the center of a lane at the acceptance sample location. A core shall not be taken over dowels or within 5 ft of a header. One 4 in. diameter full depth core shall be taken from the pavement for each subplot appealed. All core holes shall be filled with PCC or rapid setting patch material within 24 h of drilling.

The air content for a subplot will be the hardened concrete air content determined from the core in accordance with ITM 401. When ACBF aggregates are used, the hardened concrete air content will be determined in accordance with ASTM C 457.

The cost of corrections for pavement smoothness and re-texturing shall be included in the cost of QC/QA-PCCP.

The cost of coring and refilling of the pavement holes for appeals shall be included in the cost of QC/QA-PCCP.

730 Traffic control for appeals shall be supplied with no additional payment.

Removal and replacement of QC/QA-PCCP damaged by freezing shall be with no additional payment.

SECTION 502 – PORTLAND CEMENT CONCRETE PAVEMENT, PCCP

502.01 Description

This work shall consist of portland cement concrete pavement, PCCP, placed on a prepared subgrade or subbase in accordance with 105.03.

MATERIALS

502.02 Materials

10 Materials shall be in accordance with the following:

Admixtures	912.03
Coarse Aggregate, Class AP, Size No. 8	904
Fine Aggregate, Size No. 23.....	904
Fly Ash	901.02
Ground Granulated Blast Furnace Slag	901.03
Portland Cement	901.01(b)
Rapid Setting Patch Materials	901.07
Water	913.01

20

502.03 Concrete Mix Design

A concrete mix design submittal, CMDS, shall be in accordance with 502.04. The CMDS shall be submitted one week prior to production and approved by the Engineer. The CMDS shall be submitted utilizing the Department provided spreadsheet and shall include the following:

- (a) a list of all ingredients
 - (b) the source of all materials
 - (c) the fine to total aggregate ratio
 - (d) the absorption of the aggregates
 - (e) the SSD bulk specific gravity of the aggregates
 - (f) the specific gravity of pozzolan
 - (g) the batch weights
 - (h) the names of all admixtures
- 30

502.04

- (i) the admixture dosage rates and the manufacturer's recommended range.

Production may commence once the DTE approves the submission as a CMDP.

40 Any of the following changes or adjustments to an existing CMDP shall require a new CMDS to be submitted to the DTE.

- (a) cement source or type
- (b) pozzolan source or type
- (c) aggregate source or type
- (d) admixture source or type
- (e) addition or deletion of an admixture
- (f) proportioning of the concrete in accordance with 502.04 as follows:

50

1. cement content or cement reduction
2. pozzolan to cement substitution ratio
3. target water/cementitious ratio
4. proportion of aggregate by weight exceeding $\pm 2\%$.

A CMDP in accordance with 501.05 or a CMDP in accordance with 502.04 from a previous contract may be submitted for use upon the approval to the DTE.

502.04 Concrete Mix Criteria

60 The fine aggregate shall be at least 35% but not more than 45% of the total weight of the aggregate in each cubic yard. Proportions will be based upon saturated surface dry aggregates.

(a) Portland Cement Concrete

The CMD shall produce workable concrete mixtures, with the minimum amount of water, and having the following properties.

	Portland cement content	564 lbs/cu yd
	Maximum water/cementitious ratio	0.450
70	Maximum cement reduction for GGBFS replacement ...	30%
	Fly Ash/portland cement substitution ratio	1.25 by weight
	Maximum cement reduction for fly ash replacement	20%
	GGBFS/portland cement substitution ratio	1.00 by weight
	Slump, formed	2 to 6 in.
	Slump, slipformed	1.25 to 3 in.
	Air	5.0% to 8.0%
	Minimum flexural strength, third point	
	loading, with fly ash	550 psi at 28 days
	Relative yield	0.98 to 1.02

80

Class C concrete in accordance with 702 using Class AP coarse aggregate may be substituted in PCCP.

Chemical admixtures type A, type B, type C, type D, type E, and type F may be allowed with prior written approval.

90 Fly ash or GGBFS used as an additive, or blended cements may only be incorporated in the concrete mix between April 1 and October 15 of the same calendar year. If type IP, type IP-A, type IS or type IS-A cements are to be used, the portland cement content shall be increased to 598 lbs/cu yd. The use of fly ash or GGBFS as an additive will not be allowed when blended cement types IP, IP-A, IS, or IS-A are used.

(b) High-Early Strength Concrete

100 The Contractor shall submit, along with the CMDS, all supporting test results for approval to the DTE prior to placing concrete. Testing shall be conducted by an American Concrete Institute, ACI, certified concrete field testing technician, grade 1. The supporting test results shall be signed by the technician and include air content, slump, relative yield, water cement ratio, and the flexural strengths at 1 day, 2 days, and 7 days.

The CMD shall produce workable concrete mixtures, with the minimum amount of water, and having the following properties.

	Minimum portland cement content (types I, IL or III) ...	564 lbs/cu yd
	Maximum fly ash addition.....	10% of cement content
	Maximum water/cementitious ratio (types I or IL).....	0.42
	Maximum water/cementitious ratio (type III).....	0.45
	Maximum GGBFS addition.....	15% of cement content
	Slump, formed	2 to 6 in.
110	Slump, slipformed	1.25 to 3 in.
	Air content.....	5.0% to 8.0%
	Minimum flexural strength, third point loading	550 psi at 2 days
	Relative yield.....	0.98 to 1.02

Fly ash or GGBFS used as an additive may only be incorporated in the concrete mix between April 1 and October 15 of the same calendar year.

Chemical admixtures type A, type B, type C, type D, type E, and type F may be allowed with prior written approval.

120 **502.05 Job Control**

Control of PCCP for air content, slump, or relative yield will be determined on the basis of tests performed by the Engineer in accordance with 505. Concrete and necessary labor for sampling shall be furnished as required by the Engineer. Testing will be in accordance with the Frequency Manual.

502.06

130 The Engineer will notify the Contractor when test results for air content, slump, or relative yield are outside the requirements of 502.04. Rounding will be in accordance with 109.01(a). The Contractor shall adjust the mixture such that it is in accordance with 502.04.

CONSTRUCTION REQUIREMENTS

502.06 General

Equipment for PCCP shall be in accordance with 508.

140 Aggregate stockpiles shall be located in well drained areas to prevent the soil from pumping into and contaminating the aggregate that is to be used in PCCP. Stockpiles shall be built in layers not to exceed 6 ft. Upper layers shall be prevented from spilling onto the lower layers.

Aggregate stockpiles shall be worked to minimize segregation and maintain uniform moisture content. Aggregates which have become contaminated shall not be used.

The water measuring device will be checked under actual working conditions or at any other time deemed necessary. All labor and equipment required for calibrating and checking shall be furnished.

150 The volume of the batched concrete shall not exceed the manufacturer's standard rating for the concrete mixer.

502.07 Preparation of Grade

The subgrade shall be shaped to the required grade and section, free from all ruts, corrugations, or other irregularities, and uniformly compacted and approved in accordance with 207. Surfaces on which a mixture is placed shall be free from objectionable or foreign materials at the time of placement.

502.08 Preparation of Subbase

160 Subbase, if required, shall be placed and shaped to the required grade and section in accordance with 302. Construction traffic shall not be allowed on the aggregate drainage layer of the subbase, except where PCCP placement is restricted. Exceptions shall be submitted for approval.

502.09 Placement

Placement of PCCP shall be by the slipformed or formed methods with equipment specified in 508.04. The subgrade or subbase shall be uniformly moist at the time of PCCP placement. Excessively dry subgrade or subbase shall be sprinkled with water.

170 If the slip-form method is used the subgrade or subbase shall firmly support the paving equipment to construct the specified alignment and grade. The slip-form paver shall be operated with as nearly a continuous forward movement as possible. If it is

necessary to stop the forward movement of the paver, the vibratory and tamping elements shall also be stopped. Edge slump of PCCP shall not exceed 1/4 in.

When the slip-form method is used, the Contractor shall have metal or wood forms available for protection of the PCCP edges should excessive edge slump occur.

180 If forms are used they shall be firmly supported by the subbase or subgrade for the entire length of the form at the specified alignment and grade. The alignment of the forms shall not deviate more than 1/4 in. in the horizontal direction from the planned PCCP width for tangent sections.

Forms shall be staked into place with a minimum of three pins for each 10 ft section. A pin shall be placed at each side of every joint. Form sections shall be locked tightly and be free from play or movement in any direction. No excessive settlement or springing of forms under the finishing machine will be allowed. Forms shall be cleaned and oiled prior to the placing of concrete.

190 Forms shall be kept a minimum of 500 ft ahead of concrete placement when distance allows. Any material displaced during form setting operations shall be thoroughly compacted. If material under the forms becomes unstable before concrete is placed, the forms shall be removed, the grade corrected, and the forms reset.

502.10 Concrete Mixing and Transportation

200 Concrete mixing and transportation shall be completed by central mixed, shrink mixed, or transit mixed methods. The minimum batch of concrete shall be 2 cu yd. When the concrete temperature is 90°F or above, discharge from non-agitating equipment shall be completed within 30 minutes of mixing the water, cement, and aggregates. For concrete temperature below 90°F, discharge from non-agitating equipment shall be completed within 45 minutes of mixing the water, cement, and aggregates. The concrete temperature will be measured in accordance with ASTM C 1064 at the point of delivery. Discharge from a truck agitator or a truck mixer shall be completed within 90 minutes of mixing the water, cement, and aggregates.

210 Concrete shall be uniformly mixed when delivered to the job site. Batch tickets for each load of PCC shall indicate the weight of cement, pozzolan, and aggregates, volume or weight of water, and the type and volume of admixtures. The weight of the cement shall be within 1% of the CMDP, the saturated surface dry weight of the aggregates shall be within 2% of the CMDP, and the volume or weight of water shall be within 1% of the required amount.

The Engineer may conduct additional testing to verify uniformity of the mixture. Additional testing will consist of slump tests taken in accordance with AASHTO T 119 at approximately the 1/4 and 3/4 points of a load. If the slumps differ by more than 1 in. when the average slump is 3 in. or less, or by more than 2 in. when the average slump is greater than 3 in., paving operations may be suspended while the mixing process is jointly reviewed and problems resolved by the Engineer and the Contractor.

220

Wash water shall not be used as a portion of the mixing water.

When concrete is delivered in transit mixers, additional water to increase the workability of a load may be added within 45 minutes of initial mixing. Any addition of water shall be noted on the batch ticket and shall not occur as a continuing operation.

230

Stationary mixers shall be operated at the manufacturer's recommended drum speed. Batches shall not exceed the nominal capacity of the mixer. A maximum overload of 10% may be allowed provided strength and consistency remain satisfactory and no spillage of concrete takes place.

(a) Central Mixed Concrete

Central mixed concrete shall be completely mixed in a stationary mixer and transported in a truck agitator, truck mixer at agitating speed, or non-agitating equipment.

240

Mixing for central mixed concrete shall be no less than 60 s per batch. The mixing time shall be measured from the time all cement and aggregates are in the drum. The batch shall be so discharged into the mixer that some of the water enters in advance of the cement and aggregates. All required water shall be in the drum by the end of the first quarter of the specified mixing time.

If a truck mixer or truck agitator is used for transportation, the concrete shall be agitated at the agitation speed designated by the manufacturer.

(b) Shrink Mixed Concrete

Shrink mixed concrete shall be partially mixed in a stationary mixer and the mixing completed at the plant in a truck mixer.

250

The time in a stationary mixer for shrink mixed concrete may be reduced to approximately 30 s. Mixing shall then be completed in a truck mixer at the plant by 50 to 100 revolutions of the drum at the mixing speed designated by the manufacturer. Agitation during transportation shall be at the agitation speed designated by the manufacturer.

(c) Transit Mixed Concrete

Transit mixed concrete shall be completely mixed and transported in a truck mixer.

260

Mixing for a truck mixer loaded to rated capacity shall be 70 to 100 revolutions of the drum at the mixing speed, but not less than the number of revolutions recommended by the manufacturer. Discharge shall be completed prior to 300 revolutions of the drum.

502.11 Weather Limitations

PCCP shall not be placed on a frozen subgrade or subbase. PCCP operations shall

not begin until the ambient temperature is 35°F and rising. PCCP operations shall be discontinued when the ambient temperature is descending and is 40°F or below. PCCP operations may occur outside these temperatures when authorized in writing.
 270 Regardless of placement temperature, sufficient means shall be taken to prevent the PCCP from freezing prior to attaining opening to traffic strengths in accordance with 502.18. Any PCCP damaged by freezing shall be removed and replaced.

When concreting is authorized during cold weather, the aggregates may be heated by either steam or dry heat prior to being placed in the mixer. The apparatus used shall heat the mass uniformly and prevent the occurrence of overheated areas which might damage the materials. Unless authorized, the temperature of the mixed concrete shall not be less than 50°F and not more than 80°F at the time of placement.

280 When the water or the aggregates are heated, they shall be a minimum of 70°F or a maximum of 150°F. When either aggregates or water are heated to above 100°F, they shall be combined in the mixer before the cement is added.

502.12 Placing Concrete

The batches shall be deposited so as to have a uniform mix and require as little rehandling as possible. The plastic concrete shall not be segregated during placement. Rakes shall not be used to handle plastic concrete. Dowel bars and assemblies shall not be displaced during placement of concrete. Plastic concrete shall not be contaminated with earth or other foreign matter.

290 Concrete shall be thoroughly consolidated against the faces of all forms or adjacent concrete surfaces. Hand placed concrete shall be thoroughly consolidated with the use of a vibrator. Vibrators shall not operate in any one location so as to bring excessive mortar to the surface, and shall not come in contact with a dowel bar assembly, subgrade, subbase, or forms.

Concrete shall be placed around manholes or similar structures in accordance with 720.

300 The Contractor shall be responsible for the protection of the existing joints from the intrusion of fresh concrete mortar, and for all damage to existing pavement caused by the operation of mechanical equipment. Concrete materials that fall on or are worked into the joints or surface tines of an existing slab, shall be removed immediately.

Concrete shall not be mixed, placed, or finished when the natural light is insufficient, unless an adequate and approved artificial lighting system is operated.

310 The Contractor shall have available at all times sufficient materials for the protection of unhardened PCCP from the effects of rain. Covering material such as burlap or polyethylene sheeting shall be provided. When rain appears imminent, paving operations shall stop. All available personnel shall be used to cover the PCCP.

502.13 Joints

Joints shall be in accordance with 503.

502.14 Finishing

PCCP shall be finished in accordance with 504.

320

502.15 Curing

PCCP shall be cured with an approved white pigmented liquid membrane forming compound. Alternative methods of curing may be approved by the Engineer. Curing shall be in accordance with 504. For formed PCCP, immediately after the forms are removed, the sides of the PCCP shall be cured.

502.16 Form Removal

Forms may be removed as soon as the PCCP has hardened sufficiently to prevent edge spalling or other damage. Form pullers shall not be supported on the PCCP during form removal operations.

330

502.17 Pavement Inspection

The Contractor and the Engineer will conduct an inspection of the new PCCP for any damage, including freezing or random cracks. The inspection and all necessary repairs shall be completed prior to opening the pavement to non-construction traffic. All random, full-depth cracks in the PCCP shall be corrected in accordance with 503.06. All other damages shall be repaired by approved methods.

502.18 Opening to Traffic

340

When fly ash, GGBFS, or cement type IP, type IS, type IP-A, or type IS-A is incorporated into the PCCP, traffic shall not be allowed on the PCCP until the test beams indicate a modulus of rupture of 550 psi or greater. Opening to traffic of PCCP not containing the above additives shall be based on the following.

(a) Construction

Construction vehicles or equipment may be allowed on the PCCP after 10 days or when the test beams indicate a modulus of rupture of 550 psi or greater. Any construction vehicle or equipment that may damage the PCCP shall not be used on the PCCP unless adequate protection is provided. Approved joint cutting saws may be operated on the PCCP as determined by the Contractor.

350

(b) Non-Construction

PCCP may be opened to traffic after 14 days or when test beams indicate a modulus of rupture of 550 psi or greater. Prior to opening to traffic, cracks and joints shall be sealed in accordance with 503.05 and the PCCP shall be cleaned.

502.19 Pavement Corrugations

Pavement corrugations shall be in accordance with 606.

502.20 Pavement Smoothness

360 Pavement smoothness will be in accordance with 501.25 except profilograph requirements will not apply.

502.21 Pavement Thickness

370 PCCP thickness shall be determined after all corrective grinding. The Contractor shall obtain cores at the locations determined by the Engineer in accordance with ITM 802. Cores, 4 in. in diameter, shall be taken in the presence of the Engineer for the full depth of the PCCP. The Engineer will take immediate possession of the cores. Cores shall not be taken within 2 ft of the edge of PCCP, over dowels, or within 5 ft of a transverse construction joint. Cores shall be taken and measured in accordance with ITM 404. All core holes shall be filled with PCC or rapid setting patch material within 24 h of drilling.

If a core measurement reveals that the pavement is more than 1/2 in. deficient in thickness, additional cores shall be drilled at 20 ft intervals on each side of the original core. These additional cores shall be on a line which passes through the original core and parallel to the centerline of the pavement. The drilling shall continue in both directions at 20 ft intervals until two successive cores indicate a thickness deficiency of 1/2 in. or less, or where cores can no longer be drilled in the new PCCP.

380 If a core indicates a thickness deficiency of more than 1 in. and two cores drilled adjacent at 20 ft intervals indicate a thickness deficiency of not more than 1 in., additional cores shall be drilled at 5 ft intervals on each side of the initial core. The drilling shall continue in both directions at 20 ft intervals until two successive cores indicate a thickness deficiency of 1/2 in. or less, or where cores can no longer be drilled in the new PCCP.

390 When a single core indicates a thickness deficiency of more than 1 in., or if two or more adjacent cores indicate a thickness deficiency of more than 1/2 in., the investigation will be expanded to include adjoining PCCP. The additional cores shall be taken from the adjoining traffic lanes or shoulders at the same station at which the first core or cores indicated the deficiency, whether the lane was paved at the same time or not.

The width of adjudicated PCCP shall be the width of pavement lane in which the deficiency occurs. Pavement that has been replaced shall be investigated for thickness.

(a) Sections

400 The quantity of PCCP for each pay item will be defined as a section. The section will be divided into subsections of 1,200 sq yd. Sections less than 1,200 sq yd shall not be cored. A minimum of one core shall be drilled at a random location within each subsection. A section greater than or equal to 1,200 sq yd shall have a minimum of four cores drilled. Partial subsections shall not be cored unless otherwise directed. Widening of 3 ft or less shall not be cored unless otherwise directed. Formed drives shall not be cored unless otherwise directed. Verification of the required pavement

depth on formed drives shall be checked in the presence of the Engineer prior to pouring, by making stringline measurements every 10 ft across the width of the drive. Any location deficient in thickness by 1/4 in. or more shall be corrected prior to placing PCCP.

410 **(b) Average PCCP Thickness**

The thickness of the PCCP for each section shall be the average lengths of all cores from the section. However, no cores shall be included from areas for which no payment will be made. Where PCCP has been removed and replaced the initial core lengths will be discarded and the core lengths of the replaced PCCP will be substituted. Any core measurements exceeding the specified PCCP thickness by more than 1/2 in. will be recorded as the specified PCCP thickness plus 1/2 in. Calculations shall be to the nearest 0.1 in.

(c) PCCP Adjusted Payment

420 If the average PCCP thickness is equal to or greater than the specified thickness, no adjustments will be made. If an average PCCP thickness is less than the specified thickness by up to 1/2 in., payment for that section will be adjusted in accordance with the following:

$$Q_T = Q \times U \times (1 - M^2/S^2)$$

where:

Q_T = quality assurance assessment for thickness

Q = placed quantity of the PCCP section

M = average PCCP thickness of the section

S = specified PCCP thickness of the section

U = unit bid price.

(d) PCCP Non-Payment

430 Where two adjacent cores indicate a thickness deficiency of more than 1/2 in., no payment will be made unless the PCCP is removed and replaced. Payment for PCCP with non-adjacent cores indicating a thickness deficiency of more than 1/2 in. will be in accordance with 502.21(c).

The limits of non-payment shall extend from deficient core to the transverse joint location nearest the first additional core indicating a thickness deficiency of less than 1/2 in.

(e) PCCP Removal

440 Where two adjacent cores indicate a thickness deficiency of more than 1 in. the PCCP shall be removed and replaced. Non-adjacent cores indicating a thickness deficiency of more than 1 in. do not require removal and replacement.

The limits of removal and replacement shall extend from the deficient core to the transverse joint location nearest the first additional core indicating a thickness deficiency of less than 1/2 in.

503.01

No additional payment will be made for PCCP which has an average thickness above that shown on the plans.

The cost of trial batch demonstrations shall be included in the cost of PCCP.

500 The cost of corrections for pavement smoothness and re-texturing shall be included in the cost of PCCP.

Removal and replacement of PCCP found to be deficient or damaged by freezing shall be completed with no additional payment.

The cost of coring and refilling of the pavement holes for appeals shall be included in the cost of PCCP.

SECTION 503 – PCCP JOINTS

503.01 Description

This work shall consist of the construction of joints in PCC pavements, placing dowel bar assemblies and joint sealing operations in accordance with 105.03.

MATERIALS

503.02 Materials

10 Materials shall be in accordance with the following:

Chemical Anchor System	901.05
Dowel Bars	910.01(b)10
Epoxy Coated Reinforcing Bars	910.01(b)9
Joint Filler	906.01
Joint Materials	906
PCC Sealer/Healers	901.06
Reinforcing Bars.....	910.01

20 Tie bars shall be epoxy coated reinforcing bars.

Bent tie bars shall be deformed billet steel in accordance with 910.01 and ASTM A 615, grade 40.

The epoxy coating on the bent and straight tie bars shall be protected in accordance with 703.04.

CONSTRUCTION REQUIREMENTS

30 503.03 Joints

Joints shall be constructed in accordance with the type and dimensions and at the

locations shown on the plans or as directed. All joints shall be perpendicular to the subgrade.

Longitudinal joints shall be parallel to the centerline. The longitudinal joint shall not deviate from the true line shown on the plans by more than 1/4 in. Transverse joints shall be at right angles to the centerline and be continuous for the full width of the pavement.

- 40 All joints shall be cut to the required dimensions and sealed. All sawed joints shall be made by sawing equipment in accordance with 508.07 and shall be in accordance with the following.

(a) Type D-1 Contraction Joint

Type D-1 contraction joints shall be created by sawing slots in the pavement unless alternative methods are approved. The sawed contraction joint spacing shall be as shown on the plans or as directed, but shall not exceed 18 ft.

- 50 Sawed contraction joints shall be cut in two operations. The initial saw cut shall commence as soon as the concrete has hardened sufficiently to enable sawing without raveling, usually 2 to 12 h after placement. All joints shall be saw cut through the edges of the pavement to the required depth before uncontrolled shrinkage cracking takes place. The sawing operations shall be carried on during day and night, regardless of weather conditions. The sawing of a joint shall be omitted if a crack occurs at or near the joint location prior to the time of sawing. Sawing shall be discontinued if a crack develops ahead of the saw. Formed contraction joints may be used where conditions make sawing impractical.

- 60 The second saw cut shall be made after the concrete has sufficiently cured, but before opening the pavement to non-construction traffic. Slurry or saw residue remaining in the slot shall be immediately flushed with water. Construction traffic shall not be allowed on the PCCP after the second saw cut until the joint is sealed.

The sawed slot shall be cleaned to remove all foreign matter from the entire depth of cut. Joint sealing shall be in accordance with 503.05.

(b) Longitudinal Joint

- 70 Longitudinal joints shall be created by sawing slots in the pavement unless alternative methods are approved. The longitudinal joint spacing shall be as shown on the plans or as directed, but shall not exceed 16 ft. Tie bars shall be placed by mechanical equipment in accordance with 508.04(a), or rigidly secured in place.

Longitudinal joints shall be cut to the depth, width, and line shown on the plans. The longitudinal joint slots shall be sawed concurrently with the initial D-1 contraction joint slots. If random cracking occurs ahead of sawing, the sawing operations shall be discontinued in that area. A second saw cut shall be made when construction traffic uses the PCCP prior to sealing. Joint sealing shall be in accordance with 503.05.

80 Longitudinal joints may be replaced with longitudinal construction joints when approved by the Engineer.

(c) Transverse Construction Joints

Transverse construction joints shall be constructed when there is an interruption of more than 30 minutes in the PCCP placement operations. A transverse construction joint located at a D-1 contraction joint shall be in accordance with 503.03(a), except the initial saw cut shall be omitted. All other transverse construction joints shall be located at least 6 ft from an adjacent D-1 contraction joint.

90 Tie bars for transverse construction joints may be placed in the plastic or hardened concrete. A header board with openings for tie bars shall be used when placing tie bars in plastic concrete. The header board shall be rigid and accurately set to grade. Tie bars placed in hardened concrete shall be retrofitted in accordance with 503.03(g).

(d) Longitudinal Construction Joint

The longitudinal construction joint spacing shall be as shown on the plans or as approved. Tie bars shall be placed by mechanical equipment in accordance with 508.04(a) or other approved methods. Longitudinal construction joint saw cuts may be made as soon as the PCCP has sufficiently hardened.

100 Longitudinal construction joints shall be cut to the depth, width, and line shown on the plans. Construction traffic shall not be allowed on the PCCP after the saw cuts are made until the joints are sealed. Joint sealing shall be in accordance with 503.05.

Bent tie bar spacing shall be adjusted to prevent interference with the D-1 contraction joints. Bent tie bars shall not be omitted. Bent tie bars shall be replaced with retrofitted tie bars when more than one tie bar breaks within 30 ft during straightening.

110 The longitudinal construction joint for shoulder widths less than 6 ft may be replaced by a longitudinal joint or be eliminated by extending the type D-1 contraction joint through the shoulder. If either option is used, the mainline and shoulder shall be constructed at the same time.

(e) Terminal Joints

120 Terminal joints shall consist of a sleeper slab, polyethylene bond breaker, and HMA mixtures. The polyethylene bond breaker shall be an approved polyethylene sheeting having a thickness of 6 mils or greater. HMA mixtures shall consist of type B surface and intermediate mixtures in accordance with 402.04. A MAF in accordance with 402.05 will not apply. Aggregate requirements of 904.03(d) do not apply. The portion of the sleeper slab on which the polyethylene bond breaker is to be placed shall be finished to a smooth trowel finish.

(f) Expansion Joints

Expansion joints shall be constructed at the locations shown on the plans and shall consist of joint filler.

The joint filler shall be shaped to the subgrade, parallel to the surface, and be full width of the pavement. Damaged or repaired joint filler shall not be used.

- 130 The joint filler shall be held in a position which is normal to the surface. Finished joints shall deviate no more than 1/4 in. in the horizontal alignment from a straight line. There shall be no offsets between adjacent sections when the joint filler consists of more than one section. No plugs of concrete shall be within the expansion joint.

(g) Retrofitted Tie Bars

- 140 Retrofitted tie bars shall be secured at right angles to the pavement with a chemical anchor system in accordance with the manufacturer's recommendation. The chemical anchor system shall be injected to the back of the hole to eliminate air pockets prior to inserting the bar. The quantity of material injected shall be sufficient to disperse the material along the entire length of the bar and completely fill the annular space. After the anchor system has been injected, the bar shall be fully inserted using a back-and-forth twisting motion, leaving the proper length exposed. If it is necessary to use a hammer to seat the bar, the exposed end shall be protected with a wood block.

- 150 When a capsule type chemical anchor system is used, the capsules shall be conditioned as per the manufacturer's installation instructions, if required, and placed at the back of the hole. The number of capsules shall be sufficient to disperse the material along the entire length of the bar and completely fill the annular space. After the capsules have been placed the bar shall be fully inserted in accordance with the manufacturer's installation instructions.

503.04 Dowel Bar Assemblies

The dowel bar assemblies shall be in accordance with the following:

- 160 (a) The dowel bars shall be supported by an approved welded wire assembly which shall hold the bars rigid during placement of the PCCP. The wire for the welded assembly shall be in accordance with ASTM A 82. The maximum angle of deviation shall not exceed 1 in 48 units during placement.
- (b) The assembly shall have two continuous parallel spacer bars and two continuous parallel bearing members of size W 7.5 or greater. One spacer bar shall be located at or near each end of the dowel. Alternate ends of dowels shall be welded to a spacer bar so that the dowels remain parallel to each other and enable sliding movement in the joint. The free ends of each dowel shall be retained securely in place by means of wire loops.

- 170 (c) Suitable struts or tie wires shall be provided to hold the assembly in correct position during installation. The tie wires shall be size W 7.5 or smaller and there shall be a maximum of five tie wires for each dowel bar assembly.
- (d) The assembly shall have an upright support welded to the spacer bar and a continuous bearing member at the end of each dowel.
- (e) If the upright support consists of a single vertical wire, the support shall be size W 7.5 or greater wire. Otherwise, the support shall be 1/4 in. or greater in diameter.
- 180 (f) At the time of placement, dowel bars shall be free of dirt, loose rust, or scale. If the Engineer suspects the epoxy coating has been damaged by exposure to ultraviolet light, a sample will be obtained and will be tested in accordance with 910.01(b)9.
- (g) The dowel bar assembly shall be held securely in place during placing, consolidating, and finishing the PCCP by means of metal pins. Pins used on granular subbase shall penetrate a minimum of 12 in. below the dowel bar assembly. Pins shall be size W 7.5 or greater wire and shall be provided with a hook or arm welded to the pin so that it shall secure the assembly in place. A minimum of eight pins shall be used for each 10, 11, or 12 ft section of assembly. A minimum of 10 pins shall be used for assembly sections greater than 12 ft and less than or equal to 16 ft.
- 190 (h) Dowel bars shall be coated with a bond breaking material and the coating shall be evident at the time of placement of the PCCP.
- 200 (i) Dowel bars shall be placed 6 in. from the edges of the pavement and spaced at 1 ft on center across the joint.

503.05 Sealing Cracks and Joints

Cracks and joints in the PCCP shall be cleaned and sealed in accordance with the sealant manufacturer's recommendations. Water blasting shall not be applied under pressure which may damage the concrete. All cracks and joints shall be sealed prior to discontinuing work for the winter.

- 210 When preformed elastomeric joint seals are used, the material shall be installed in one continuous piece by means of an approved machine. The seal shall not be stretched more than 5% while being placed and show no twisting, rollover, folding, cutting, or excess lubricant-adhesive on the top of the seal. Elastomeric joint seal may be installed in two separate pieces for phased construction with the splice point occurring at the

highest point of the joint. The splicing method used shall be in accordance with the seal manufacturer’s recommendations.

503.06 Random Crack Remediation

Random cracks shall be corrected.

220

(a) Transverse

Random transverse cracks shall be corrected by PCCP replacement. The replacement shall be full lane width and a minimum of 6 ft in length. Transverse PCCP removal limits shall be perpendicular to the centerline and shall include the entire random crack. Load transfer for the replacement PCCP shall be obtained by using dowel bars and retrofit epoxy coated tie bars. PCCP replacement areas shall have dowel bars which match contraction joints in any adjacent panels. All remaining panels shall be a minimum of 6 ft in length.

230

(b) Longitudinal

Random longitudinal and skewed cracks within 18 in. of a longitudinal joint shall be routed and sealed. All longitudinal saw cuts in areas of random cracks shall be sealed with a sealer/healer or a bonding agent in accordance with ASTM C 881, grade 1.

Random longitudinal and skewed cracks outside 18 in. of a longitudinal joint shall be corrected by PCCP replacement in accordance with 503.06(a).

503.07 Method of Measurement

240

D-1 contraction joints and terminal joints will be measured by the linear foot as measured along the centerline of the joint.

Retrofitted tie bars will be measured by the number of units installed.

503.08 Basis of Payment

D-1 contraction joints and terminal joints will be paid for at the contract unit price per linear foot, complete in place.

250

Retrofitted tie bars will be paid for at the contract unit price per each, complete in place.

Payment will be made under:

Pay Item	Pay Unit Symbol
D-1 Contraction Joint	LFT
Retrofitted Tie Bars	EACH
Terminal Joint.....	LFT

504.01

260 The cost of furnishing and placing all materials, not specified as a pay item, shall be included in the cost of PCCP.

The cost of dowels, dowel bar assemblies, backer rod, joint sealants and all necessary incidentals shall be included in the cost of D-1 contraction joints.

The cost of the sleeper slab, reinforcing bars, bond breaker, and HMA mixtures shall be included in the cost of the terminal joint.

270 The cost of retrofitted tie bars or PCCP replacement used to repair damaged PCCP due to fault or negligence, remediation of random cracking, or the replacement of broken deformed bars shall be included in the cost of the PCCP.

SECTION 504 – PCCP FINISHING AND CURING

504.01 Description

All PCCP surfaces shall be finished and cured in accordance with the following.

MATERIALS

504.02 Materials

The materials shall be in accordance with the following:

10

Curing Materials.....912.01

CONSTRUCTION REQUIREMENTS

504.03 Finishing

PCCP shall be finished with equipment in accordance with 508.04. The operations shall be controlled so that an excess of mortar and water is not worked to the top. Long handled floats may be used to smooth and fill in open textured areas in the PCCP.

20

Hand methods of finishing may be used when finishing equipment breaks down or in tight working areas where field conditions limit the use of mechanical devices. Hand placed concrete shall be further finished by means of a longitudinal float or an approved transverse smoothing float in accordance with 508.08(a).

The edges of formed PCCP adjacent to HMA or compacted aggregate shall be tooled. A continuous radius with a uniform smooth dense mortar finish shall be produced.

30

The PCCP surface shall be textured with a double thickness burlap drag or a minimum 4 ft wide turf drag.

The textured surface of PCCP shall be tined, unless otherwise specified. Tining shall consist of transverse grooves that are between 3/32 and 1/8 in. in width, between 1/8 and 3/16 in. in depth, and be spaced as follows: 5/8 in., 1 in., 7/8 in., 5/8 in., 1 1/4 in., 3/4 in., 1 in., 1 in., 1 in., 1 in., 3/4 in., 7/8 in., 1 3/4 in., 7/8 in., 3/8 in., 1 in., 1 in., 1 1/4 in., 1 1/2 in., 7/8 in., 3/4 in., 7/8 in., 1 in., 7/8 in., 1 in. The grooving pattern shall be repeated across the pavement. The grooves shall be formed in the plastic concrete without tearing the surface and without bringing pieces of the coarse aggregate to the top of the surface.

40

Texturing and curing operations may be performed by a single machine subject to satisfactory performance.

Areas of PCCP which are not finished in accordance with these requirements shall be corrected by retexturing.

50

Retexturing shall consist of cutting longitudinal or transverse grooves in the PCCP surface by means of saw blades or other approved devices. The grooves shall be spaced 3/4 in. center to center and be 1/8 in. in width and depth. Alternative patterns may be used, subject to approval. The PCCP surface, after cutting, shall not be polished.

504.04 Curing

Curing materials shall be applied to exposed surfaces and sides of newly placed PCCP within 30 minutes after the finishing operations have been completed, or as soon as marring of the concrete does not occur. Paving operations shall be immediately suspended if sufficient curing materials are not available on site.

60

When forms are used, the edges of the pavement shall be cured immediately upon removal of the forms. The edge shall be covered with curing materials equal to the material used on the surface or banked with soil 12 in. wide or greater.

When conditions arise which prevent immediate application of curing materials, the paving operation shall be suspended and the PCCP shall be kept wet with a fine spray of water. The fine spray of water shall continue until application of curing materials resumes.

Curing shall be continuous for 96 h unless a longer period is ordered and shall be in accordance with the following.

70

(a) Liquid Membrane Forming Compounds

Immediately after surface water has disappeared, a uniform coating of the liquid membrane forming curing compound shall be applied.

The compound shall be applied in a continuous uniform film at a rate not less than 1 gal./150 sq ft. It shall be applied in two applications. The curing compound may be warmed in a water bath during cold weather at a temperature not exceeding 100°F. Thinning with solvents will not be allowed. Non-uniform film rates will result in the discontinuance of that application method.

- 80 A new coat of curing compound shall be applied to areas damaged by rain or other means during the curing period. The recoating shall be applied as soon as possible and at a rate equal to that specified for the original coat.

(b) Double Burlap

The PCCP shall be covered with wet burlap, laid directly on the surface, and kept wet with a fine spray of water. This initial burlap shall receive an additional covering of wet burlap no later than 9:00 a.m. the day following its placement. The two layers of burlap shall be kept wet for the required curing period.

- 90 **(c) Waterproof Covers**

The PCCP shall be kept wet with a fogged spray of water, or be covered with wet burlap laid directly on the surface and kept wet with a fine spray of water. The PCCP shall receive a cover no later than 9:00 a.m. the day following its placement. If white burlap polyethylene sheets are used, the burlap side shall be wet or the surface of the concrete thoroughly wetted just prior to the blanket being placed.

The covers shall be weighted down on each edge and shall be as wide as the full width of the pavement being cured. Adjoining covers shall overlap 12 in. or more and the laps held securely in place.

100

Covers may be reused provided they are airtight. All torn covers shall be repaired with patches. All units not in accordance with these requirements shall not be used.

The covers shall remain in place for the required curing period.

(d) Straw

- 110 The PCCP shall be covered with wet burlap, laid directly on the surface, that is kept wet with a fine spray of water. The burlap shall be removed by 9:00 a.m. the day following its placement and the surface immediately covered with straw no less than 3 in. deep. The straw shall be thoroughly saturated immediately after being placed, and kept wet for the required curing period. After the cure period, the straw shall be removed from the pavement and disposed of properly.

Straw curing shall not be used in cities or towns unless written permission is obtained.

504.05 Method of Measurement

Finishing and curing operations will not be measured for payment.

- 120 **504.06 Basis of Payment**

The cost of finishing and furnishing and placing curing materials shall be included in the cost of the PCCP.

SECTION 505 – TESTS AND PROCEDURES

505.01 Test Methods and Procedures

The following test methods and procedures shall be used with exceptions as listed below.

	Air Test.....	AASHTO T 152* or ASTM C 173**
	Flexural Strength	AASHTO T 97*
10	Making and Curing Specimens.....	AASHTO T 23*
	Sampling Fresh Concrete	AASHTO R 60
	Sieve Analysis of Aggregates.....	AASHTO T 27
	Slump	AASHTO T 119
	Specific Gravity and Absorption, Coarse Aggregate.....	AASHTO T 85
	Specific Gravity and Absorption, Fine Aggregate.....	AASHTO T 84
	Thickness of PCCP	ITM 404
	Unit Weight and Relative Yield	AASHTO T 121*
20	Water-Cementitious Ratio	ITM 403

* The concrete shall be consolidated by the method of internal vibration in beam forms or in an aluminum measure or air meter bowl, as appropriate for the test.

** If slag aggregate is used, the method and procedure for the test shall be in accordance with ASTM C 173.

30 The chosen method of concrete consolidation shall be the same for all concrete test specimens.

(a) Exceptions to AASHTO T 23

The exceptions to AASHTO T 23 for making and curing specimens in the field shall be as follows:

1. Non-watertight beam forms, molds, will be allowed.
 2. After 24 h the molded specimens are taken to the storage location and removed from the molds.
 3. Field stored beams will not require 24 ±4 h lime water soak prior to time of testing.
- 40

(b) Exceptions to AASHTO T 97

The exceptions to AASHTO T 97 for conducting a flexural test on concrete beams shall be as follows:

1. The beam size shall be measured to the nearest 1/16 in.

506.01

- 2. The test result shall be discarded when the break occurs outside the middle 1/3 of the beam.

50 **(c) Exceptions to AASHTO T 121**

The exceptions to AASHTO T 121 for determining the unit weight of concrete shall be as follows:

- 1. Weight shall be determined to the nearest 0.01 lb.

(d) Exceptions to AASHTO R 60

The exceptions to AASHTO R 60 for sampling fresh concrete shall be as follows:

- 60 1. Where job conditions dictate, the entire sample may be obtained from one portion of the load.

(e) Exceptions to AASHTO T 152

The exceptions to AASHTO T 152 for determining the air content in portland cement concrete shall be as follows:

- 70 1. The sample for aggregate correction factor shall be prepared in accordance with 6.0. The aggregate correction factor shall be determined in accordance with 8.3 and read directly from the meter.
2. The aggregate correction factor test shall be re-run for confirmation if the test results for gravel is greater than 0.4% or if the test results for crushed stone is greater than 0.6%.
3. For aggregates indicating a high correction factor, the aggregate may be washed from the concrete sample and used to determine the correction factor.

SECTION 506 – PCCP PATCHING

506.01 Description

This work shall consist of the removal and replacement of PCCP in accordance with 105.03.

MATERIALS

506.02 Materials

10 Materials shall be in accordance with the following:

Admixtures	912.03
Calcium Chloride, Type L.....	913.02
Chemical Anchor System	901.05

20

Coarse Aggregate, Class A or Higher, Size No. 11	904
Coarse Aggregate, Class AP, Size No. 8	904
Dowel Bars	910.01(b)10
Fine Aggregate, Size No. 23	904
Portland Cement	901.01(b)
Water	913.01

Coarse aggregate for partial depth patching shall be size No. 11. Coarse aggregate for full depth patching shall be size No. 8. Coarse aggregate for patching shall be stone or gravel.

A bonding agent shall be selected from the Department’s list of approved Non-Vapor Barrier Type Bonding Agents.

30 Dowel bars and dowel bar assemblies shall be in accordance with 503.04.

506.03 Concrete Mix Design

A concrete mix design submittal, CMDS, shall be in accordance with 506.04. The CMDS shall be submitted to and approved by the DTE. The CMDS shall be submitted a minimum of seven calendar days prior to the trial batch utilizing the Department provided spreadsheet and shall include the following:

- 40
- (a) a list of all ingredients
 - (b) the source of all materials
 - (c) the fine to total aggregate ratio
 - (d) the absorption of the aggregates
 - (e) the SSD bulk specific gravity of the aggregates
 - (f) the batch weights
 - (g) the names of all admixtures
 - (h) the admixture dosage rates and the manufacturer’s recommended range.

50 The CMDS is used to conduct a trial batch in accordance with 506.05. Upon completion of the trial batch, the Contractor shall submit the concrete mix design for production, CMDP. The CMDP shall be submitted to the DTE utilizing the Department furnished spreadsheet a minimum of three work days prior to production. Production shall not commence without an approved CMDP. Both the Contractor’s and Engineer’s test results from the trial batch will be included in the CMDP submittal.

A CMDP may be changed or adjusted in accordance with the following:

(a) Change in Materials

A change in a previously approved CMDP, for a given contract, to any of the following shall be submitted to the DTE as a CMDS, referencing the original CMDP.

- 60
1. cement source or type

2. pozzolan source or type
3. coarse aggregate source or type
4. admixture type.

70 A trial batch shall be conducted in accordance with 506.05, or verification of the new CMDS may be made during the first day of production by tests conducted by the Contractor and the Engineer. Production may continue until flexural strength tests are completed, provided all other properties are in accordance with 506.04. The test results shall be submitted to the DTE utilizing the Department spreadsheet no later than one day after the flexural strength test results are complete. If the flexural strength is not in accordance with 506.04, production shall stop and all PCCP patching constructed with the new CMDS will be adjudicated as a failed material in accordance with normal Department practice as listed in 105.03.

(b) Adjustments to Materials

An adjustment in a previously approved CMDP, for a given contract, to any of the following shall be submitted to the DTE as a CMDS, referencing the original CMDP.

- 80
1. admixture source
 2. admixture product of same type and from same source designated in the original CMDP
 3. fine aggregate source
 4. fine to total aggregate ratio in excess of $\pm 3\%$ from the value designated by the original CMDP
 5. Increase in cement content from amount designated in the original CMDP.

90 The new CMDS shall be submitted to the DTE utilizing the Department spreadsheet a minimum of one work day prior to production. A trial batch or verification testing is not required for approval. Production shall not commence without an approved CMDP.

(c) Other Adjustments

Other adjustments in previously approved CMDP, for a given contract, to any of the following will be allowed and DTE notification and approval prior to use is not required.

- 100
1. admixture dosage rate
 2. fine aggregate to total aggregate ratio within $\pm 3\%$ of the value designated by the original CMDP.

An approved CMDP, from another contract in the current or previous calendar year may be used on additional contracts. The CMDP shall be submitted to the DTE for review and approval prior to use.

506.04 Concrete Mix Criteria

The fine aggregate shall be at least 35% but not more than 45% of the total weight of the aggregate in each cubic yard. Proportions will be based upon SSD aggregates.

110

The CMD shall produce workable concrete mixtures, with the minimum amount of water, having the following properties:

Minimum portland cement content.....	658 lbs/cu yd
Maximum water/cement ratio.....	0.45
Minimum slump	2 in.
Air Content	6.5% ±1.5%
Minimum Flexural strength, third point loading	300 psi at 24 h
Minimum flexural strength, third point loading	500 psi at 3 days

120

When calcium chloride solution is added, a maximum of 2%, by weight of cement, shall be used. The percentage shall be reduced to 1 if the ambient temperature is above 80°F. If the mixture is used in an 805 application, calcium chloride shall not be used.

506.05 Trial Batch

A trial batch shall be produced and tested to verify that the CMD is in accordance with the concrete mix criteria. An American Concrete Institute certified concrete field testing technician, grade 1 shall be on site to direct all sampling and testing. The trial batch shall be produced at the plant prior to production. The Engineer will test the concrete’s air content and determine the water/cement ratio, and prepare and test flexural beams. The flexural strength will be determined by averaging a minimum of two beam breaks. The Engineer will provide the Contractor the results of the tests.

130

A trial batch will not be required when the total quantity of partial depth patching or full depth patching will require less than 10 cu yd of material per contract.

The trial batch shall be of sufficient quantity to allow the Engineer to perform all required tests from the same batch. Trial batch concrete shall not be used for more than one test.

140

506.06 Job Control

Control of PCCP for air content and flexural strength beams will be determined on the basis of tests performed by the Engineer in accordance with 505. Concrete and necessary labor for sampling shall be furnished as required by the Engineer. Testing for air content will be on the first load of the day and once per every 50 cu yd. Beams will be made once per every 150 cu yd and tested for compliance with 3 day flexural strength requirements.

150

The Engineer will notify the Contractor when test results for air content or flexural strength are outside the requirements of 506.04. Rounding will be in accordance with 109.01(a).

CONSTRUCTION REQUIREMENTS

506.07 PCCP Removal

PCCP removal areas will be marked. Vertical saw cuts around the perimeter of the removal areas shall be made in the PCCP. Transverse cuts shall be perpendicular to the centerline of the PCCP.

160

PCCP removal areas shall not remain open overnight. Shoulders or adjacent PCCP damaged during the removal shall be repaired as directed.

(a) Partial Depth Removal

The saw cut shall be a minimum of 1 in., to a maximum of 3 in. Removal of all unsound concrete to a minimum depth of 1 in. shall be by hand chipping tools or handheld mechanically driven equipment. Mechanical hammers shall not be heavier than a nominal 45 lb class. Mechanically driven tools shall be operated at a maximum angle of 45° from the PCCP surface. If the saw cut face is damaged, a parallel saw cut

170

1 in. outside the initial saw cut shall be made and the concrete in this area shall be removed by hand chipping.

Reinforcing bars encountered during the removal operation shall be cause for a full depth patch in accordance with 506.07(b). Wire mesh reinforcement exposed during the removal operations shall be removed.

Exposure of unsound concrete below 3 in. shall be cause for a full depth patch in accordance with 506.07(b).

180

The partial depth cavities shall be thoroughly sandblasted and, just prior to placing new concrete, cleaned of all dust, chips, and water. The air lines for sandblasting and air cleaning shall be equipped with oil traps to prevent contamination of the surfaces.

(b) Full Depth Removal

The saw cut shall be full lane width and thickness of the PCCP. After the full depth saw cut is completed, vehicle mounted removal equipment may be used to remove the concrete provided this equipment does not damage the adjacent sound concrete.

190

Removal areas in the same lane which are closer than 10 ft shall require the PCCP between these areas to be removed and replaced. If a transverse joint is located within the removal area, the limits of removal shall be increased to a minimum of 1 ft beyond the joint.

Full depth removal shall be extended until sound PCCP is encountered to allow dowel bars to be firmly anchored.

All subbase material disturbed during the removal operation shall be recompact as directed.

200

506.08 Concrete Mixing and Transportation

Concrete mixing and transportation shall be completed by central mixed, shrink mixed, or transit mixed methods. Discharge from non-agitating equipment shall be completed within 30 minutes of mixing the water, cement, aggregates, and calcium chloride solution. Discharge from a truck agitator or a truck mixer shall be completed within 90 minutes of mixing the water, cement, and aggregates or within 30 minutes of the addition of calcium chloride solution. If the location of the plant is such that this time limit cannot be met, the calcium chloride solution shall be added to the concrete in a transit mixer at the site and the concrete shall then be mixed for an additional 40 revolutions prior to discharge.

210

Concrete shall be uniformly mixed when delivered to the job site. Tickets for each load of PCC shall indicate the weight of cement, and aggregates, volume of water, and the type and volume of admixtures. The weight of the cement shall be within 1% of the CMDP and the saturated surface dry weight of the aggregates shall be within 2% of the CMDP.

Wash water shall not be used as a portion of the mixing water.

220

When concrete is delivered in transit mixers, additional water to increase the workability of a load may be added within 45 minutes of initial mixing. Any addition of water shall be noted on the ticket and shall not occur as a continuing operation.

(a) Central Mixed Concrete

Central mixed concrete shall be in accordance with 502.10(a).

(b) Shrink Mixed Concrete

Shrink mixed concrete shall be in accordance with 502.10(b).

230

(c) Transit Mixed Concrete

Transit mixed concrete shall be in accordance with 502.10(c).

506.09 Weather Limitations

Placement of PCCP patches in continuous reinforced concrete pavement shall be after 1:00 p.m. when the next day's forecasted ambient temperature is 70°F or greater, unless otherwise directed.

PCCP patches shall not be placed on frozen subgrade, subbase, or PCCP.

240

506.10 Placing Concrete

The concrete shall be placed level to the adjacent PCCP and consolidated by internal vibration. The concrete shall be hand finished in accordance with 504. Texturing and tining are not required if the PCCP is to be resurfaced with HMA or diamond ground in accordance with 507.06.

506.11

250 The PCCP patch shall be cured in accordance with 504.04(a). In addition, polyethylene film shall be placed over the patch and covered with a 4 in. layer of rigid or flexible insulation and firmly anchored. Small dimension lumber weighted with sandbags may be used, but large objects such as rocks or concrete blocks shall not be used.

The PCCP patch shall be inspected in accordance with 502.17.

For patches which are not to be overlaid and have a length greater than 20 ft, pavement smoothness will be in accordance with 501.25 except profilograph requirements will not apply.

(a) Partial Depth

260 A non-vapor barrier type bonding agent shall be applied to the vertical and horizontal surfaces prior to placing concrete. Coated surfaces shall be protected from contaminants such as dust and dirt. Contaminated surfaces shall be recleaned and recoated. The bonding agent and concrete shall be placed in accordance with the bonding agent manufacturer's recommendations. The recommended time limits will be strictly enforced.

Existing joint openings within the patch shall be maintained for the full depth of the patch by preformed joint fillers or forms. After the patch has cured, these joints shall be sawed and sealed in accordance with 503.

270 **(b) Full Depth**

Patches shall be anchored with dowel bars to the adjacent PCCP as shown on the plans. Dowel bars shall be installed using a chemical anchoring system.

Patches constructed adjacent to transverse contraction joints or random cracks that are to remain in place shall be constructed with type D-1 contraction joints. The joint shall be made continuous across the width of the PCCP to match the existing joint or random crack. Patches greater than 18 ft shall have type D-1 contraction joints in accordance with 503.

280 Concrete shall be placed around manholes or similar structures in accordance with 720.

Sawing and sealing of transverse joints may be omitted when the existing PCCP is to be overlaid as part of the contract.

506.11 Opening to Traffic

A patch may be opened to traffic in accordance with the following when calcium chloride is used.

T	H	HT	T	H	HT
40 - 42°F	30	26	61 - 63°F	14	9
43 - 45°F	27	23	64 - 66°F	14	9
46 - 48°F	24	21	67 - 69°F	14	8
49 - 51°F	21	19	70 - 72°F	14	7
52 - 54°F	19	16	73 - 75°F	14	6
55 - 57°F	16	14	above 75°F	14	5
58 - 60°F	16	11			
T = Lowest ambient temperature during placement, or the temperature of concrete at time of delivery, whichever is lower H = Time in hours to open to traffic HT = Time in hours to open to traffic when the average daily traffic is less than 10,000					

290

PCCP patches with calcium chloride may be opened to traffic sooner than specified in the above table if test beams indicate a modulus of rupture of 300 psi or greater. ITM 402 may be used as an alternative method to determine the flexural strength.

When other admixtures or admixture systems are used, the PCCP patches may be opened to traffic when flexural strength tests indicate a modulus of rupture of 300 psi or greater. ITM 402 may be used as an alternate method to determine the flexural strength.

300

506.12 Method of Measurement

Partial depth patching and full depth patching will be measured by the square yard.

D-1 contraction joints and retrofitted tie bars used in PCCP patching will be measured in accordance with 503.07.

310

PCCP removal, subbase, and subgrade excavation, when required, subbase and subgrade recompaction, non-vapor barrier bonding agent, individual dowel bars, chemical anchor system, concrete, finishing, curing, and sawing and sealing of joints will not be measured for payment.

506.13 Basis of Payment

PCCP patching will be paid for at the contract unit price per square yard for the type of patching required.

D-1 contraction joints and retrofitted tie bars used in PCCP patching will be paid for in accordance with 503.08.

320

Partial depth patches which have been directed to be full depth will be paid for at the contract unit price per square yard for PCCP patching, partial depth, plus 80% of the contract unit price per square yard for PCCP patching, full depth.

507.01

Payment will be made under:

Pay Item	Pay Unit Symbol
-----------------	------------------------

PCCP Patching, Full Depth	SYS
---------------------------------	-----

PCCP Patching, Partial Depth	SYS
------------------------------------	-----

330

The cost of PCCP removal, subbase, and subgrade excavation, when required, subbase and subgrade recompaction, non-vapor barrier bonding agent, individual dowel bars, chemical anchoring system, concrete, finishing and curing, and sawing and sealing of joints shall be included in the cost of PCCP patching.

The cost of corrections for pavement smoothness and re-texturing shall be included in the cost of PCCP patching.

340

Repair or replacement of adjacent PCCP or shoulder damaged by the Contractor shall be made at no additional cost to the Department.

SECTION 507 – PCCP RESTORATION

507.01 Description

This work shall consist of cleaning and sealing of joints and cracks, patching, profiling, underseal, and retrofit load transfer in accordance with 105.03.

MATERIALS

507.02 Materials

10 Materials shall be in accordance with the following:

Asphalt Binder, PG 64-22	902.01(a)
Dowel Bars	910.01(b)10
Fine Aggregates, Size No. 23 or 24	904
Joint Sealing Materials	906.02
Rapid Setting Patch Materials	901.07

Dowel bars and dowel bar assemblies shall be in accordance with 503.04.

20

CONSTRUCTION REQUIREMENTS

507.03 Cracks

Sealing and filling operations shall not be conducted on a wet surface, when the ambient temperature is below 40°F, or when other unsuitable conditions exist, unless approved by the Engineer.

(a) Routing, Cleaning and Sealing

30 Cracks in PCCP shall be routed and cleaned when specified. Cracks shall be routed with a routing machine capable of cutting a uniform shape to form a reservoir not exceeding 3/4 in. wide with a minimum depth of 3/4 in. The operation shall be coordinated such that routed materials do not encroach on pavement lanes carrying traffic and all routed materials are disposed of in accordance with 104.07. The cracks shall be cleaned with compressed air or by other suitable means. Air compressors shall be capable of producing a minimum air pressure of 100 psi. Water blasting shall not be utilized.

40 Cracks shall be sealed with hot poured joint sealant in accordance with the manufacturer's recommendations within 1/4 in. below the surface. A distributor in accordance with 409.03 shall be used with an indirect-heat double boiler kettle and mechanical agitator. The hot poured joint sealant shall be placed utilizing a "V" shaped wand tip, to allow the penetration of the materials into the cracks.

Application of hot poured joint sealant shall be completed without covering existing pavement markings. When traffic is to be maintained within the limits of the section, temporary traffic control measures in accordance with 801 shall be used. Treated areas shall not be opened to traffic until the hot poured joint sealant has set.

(b) Cleaning and Filling

50 The cracks shall be cleaned by blowing with compressed air or by other suitable means when specified. Air compressors shall be capable of producing a minimum air pressure of 100 psi. Water blasting shall not be utilized.

Cracks shall be filled with asphalt material. The cracks shall be completely filled or overbanded not to exceed 5 in., or as required. Asphalt material shall be placed utilizing a "V" shaped wand tip, to allow the penetration of the materials into the cracks. The filled cracks shall be covered with sufficient fine aggregate or other suitable material to prevent tracking of the asphalt material. All excess cover material shall be removed from the pavement within 24 h, when directed.

60 Application of asphalt material shall be completed without covering existing pavement markings. When traffic is to be maintained within the limits of the section, temporary traffic control measures in accordance with 801 shall be used. Treated areas shall not be opened to traffic until the asphalt material has set.

507.04 Joints

Sealing and filling operations shall not be conducted on a wet surface, when the ambient temperature is below 40°F, or when other unsuitable conditions exist, unless approved by the Engineer.

70 (a) Sawing, Cleaning and Sealing

Joints in PCCP shall be sawed, cleaned and sealed when specified. Air compressors shall be capable of producing a minimum air pressure of 100 psi. Water

blasting shall not be applied under pressure which may damage the concrete. The existing joints shall be sawed to the width and depth as shown on the plans. Slurry or saw residue remaining in the slot shall be immediately flushed with water. Traffic may be allowed on the PCCP for up to seven calendar days after the saw cutting prior to sealing.

80 Joints shall be sealed with joint sealing materials in accordance with the sealant manufacturer's recommendations. Transverse joints shall be sealed with hot poured joint sealant, silicone sealant or preformed elastomeric joint sealant. Longitudinal joints shall be sealed with hot poured joint sealant or silicone sealants.

Application of asphalt materials shall be completed without covering existing pavement markings. When traffic is to be maintained within the limits of the section, temporary traffic control measures in accordance with 801 shall be used. Treated areas shall not be opened to traffic until the asphalt material has set.

(b) Cleaning and Filling

90 Joints in PCCP shall be cleaned and filled when specified. Cleaning shall include removal of old sealant and backer rod. Air compressors shall be capable of producing a minimum air pressure of 100 psi. Water blasting shall not be utilized.

Joints shall be filled with hot poured joint sealant in accordance with the manufacturer's recommendations within 1/4 in. below the surface. A distributor in accordance with 409.03 shall be used with an indirect-heat double boiler kettle and mechanical agitator. The hot poured joint sealant shall be placed utilizing a "V" shaped wand tip, to allow the penetration of the materials into the joints.

100 **507.05 PCCP Patching**

(a) Full Depth Patching

PCCP patching shall be in accordance with 506.

(b) Partial Depth Patching

110 Partial depth patching shall be constructed at locations shown on the plans. Existing joints directed to be patched partial depth, shall be milled to a depth of 3 in. the full width of the lane. The minimum length of milling is 6 in. beyond the map-cracked area. The milled area shall be cleaned of all loose material prior to patching. Cleaning shall be by blowing the milled areas with compressed air at a minimum pressure of 100 psi. When the milled areas are satisfactorily cleaned, the milled areas shall be tacked with asphalt material in accordance with 406 and patched with HMA.

The milled areas shall be filled with HMA partial depth patching. Partial depth patches shall consist of HMA Surface, type B in accordance with 402.04. MAF in accordance with 402.05 will not apply. The mixture shall be compacted by a vibratory roller in accordance with 409.03(d). A minimum of four passes of the rollers shall be completed. Partial depth patches shall be completed during work hours and opened to

120 traffic at the close of the workday. Mixtures will be accepted in accordance with 402.09.

507.06 Profiling

130 Profiling consists of the diamond grinding of the pavement. The grinding shall be completed by mechanical grinding equipment in accordance with 508.08(c). Grinding shall be completed in a longitudinal direction and shall begin and end at lines normal to the pavement centerline in any ground section. The operation shall be coordinated such that the slurry or residue materials are continuously removed from the pavement. The slurry shall not encroach into adjacent pavement lanes carrying traffic, or flow into gutters or other drainage facilities and shall be immediately and directly deposited into a tanker truck and removed from the jobsite. Final disposal of the material shall be in an approved manner and in accordance with 104.07. Pavement smoothness will be measured and adjusted in accordance with 501.25 and 501.28(d) after the cracks are routed, cleaned, and sealed in accordance with 507.03 and joints are sawed, cleaned, and resealed in accordance with 507.04.

507.07 Undersealing

Undersealing shall be in accordance with 612.

507.08 Retrofit Load Transfer for PCCP

140 Retrofit load transfer consists of diamond saw slot cutting and placing dowel bar assemblies in the PCCP, parallel to the centerline of the roadway without damaging adjacent PCCP. The diamond-sawed slot shall be cut using two diamond saw blades per slot to cut the edges of the slot. The PCC within the slot and the burrs and bumps remaining in the base of the slots after cutting shall be removed with hand or mechanical chipping hammers which shall not exceed a nominal 15 lb in weight and shall be operated at a maximum angle of 45° from the pavement surface.

150 All surfaces of the slots shall be thoroughly cleaned by sand blasting and all cracks in the slots shall be sealed with a silicone sealer. The slots shall be cleaned and blown dry with compressed air.

Dowel bar assemblies shall be as shown on the plans. Prior to placement, the assemblies shall be coated with a bond breaking material and placed on non-metallic supports in the slots. Dowel bars shall be parallel to the pavement surface.

160 Rapid setting patch material shall be mixed and cured in accordance with the manufacturer's recommendations. The material shall be placed in the slots and troweled to match existing adjoining PCCP. Excess material removed during placing and troweling shall not be reused.

Transverse contraction joints with retrofitted load transfers shall be sawed for the full lane width and sealed in accordance with 503.03(a) except the joint shall be cut in one operation. Transverse random cracks with retrofitted load transfer slots shall be routed and sealed for the full lane width in accordance with 503.05.

PCCP damaged outside the area of the slots due to the Contractor’s operations shall be repaired in an acceptable manner or replaced.

507.09 Method of Measurement

170 Routing and sealing of cracks, filling of cracks, sawing and sealing of joints, and filling of joints will be measured by the linear foot, complete in place. Retrofit load transfer will be measured by each dowel bar assembly installed, complete in place. PCCP patching will be measured in accordance with 506.12. Profiling, regardless of depth, will be measured by the square yard. Asphalt material and drilled holes for undersealing will be measured in accordance with 612.07.

HMA partial depth patching will be measured by the ton, in accordance with 109.01(b).

180 Construction activities for the cutting, cleaning of the PCCP, dowel bars, dowel bar supports, dowel bar end caps, foam core board, patching material and all other incidentals will not be measured.

Routing of cracks or sawing of joints will not be measured. Routing and sealing of transverse random cracks at retrofitted load transfer assemblies will not be measured.

190 Temporary traffic control measures for routing, sealing or filling of cracks or sawing, sealing, or filling of joints, and profiling will be measured in accordance with 801.17.

507.10 Basis of Payment

200 Routing and sealing of cracks, filling of cracks, sawing and sealing of joints and filling of joints will be paid for by the linear foot, complete in place. The accepted quantities of retrofit load transfer will be paid for at the contract unit price per each assembly installed, complete in place. PCCP patching will be paid for in accordance with 506.13. Profiling will be paid for by the square yard. Undersealing and drilled holes will be paid for in accordance with 612.08. The accepted quantities for HMA partial depth patching will be paid for at the contract unit price per ton, complete in place.

The cost of temporary traffic control measures for routing, sealing or filling of cracks or joints, and profiling will be paid for in accordance with 801.18.

Payment will be made under:

	Pay Item	Pay Unit Symbol
	Cracks in PCCP, Filled.....	LFT
210	Cracks in PCCP, Rout and Seal.....	LFT

HMA Partial Depth Patch.....	TON
Joints in PCCP, Filled.....	LFT
Joints in PCCP, Saw and Seal	LFT
Profiling PCCP	SYS
Retrofit Load Transfer	EACH

The cost of milling, cleaning, tacking, and all incidentals shall be included in the cost of the pay item, partial depth patching.

- 220 The cost of cutting of slots, cleaning, dowel bars, dowel bar supports, dowel bar end caps, foam board, mortar, and curing materials shall be included in the cost of the pay item retrofit load transfer.

The cost of cleaning, sealing materials, and all incidentals shall be included in the cost of the pay item cracks in PCCP, filled or joints in PCCP, filled.

- 230 The cost of routing, cleaning, sealant materials, and all incidentals shall be included in the cost of the pay item cracks in PCCP, rout and seal. The cost of sawing, cleaning, sealant materials, and all incidentals shall be included in the cost of the pay item joints in PCCP, saw and seal.

The cost of all grinding, diamond cutting heads, and cleaning of the pavement, shall be included in the cost of the pay item for profiling.

SECTION 508 – EQUIPMENT

508.01 Production, Transportation, and Placement of PCC Mixtures

The Contractor shall provide and calibrate all equipment necessary for the mixing, transportation, and placement operations for PCCP.

508.02 Mixing Plant

(a) Plant Inspection

- 10 The concrete production equipment shall be capable of producing a uniform mixture. A plant inspection in accordance with 106.03 will be made by the Engineer annually, after a plant is moved, or as deemed necessary.

(b) Proportioning System

Batching plants shall be equipped to proportion aggregates and bulk cement by weight by means of automatic and interlocked proportioning devices. PCCP produced in accordance with 501 and 502 shall document each ingredient in each batch.

- 20 All scales shall be accurate to within $\pm 0.5\%$ throughout their range unless otherwise approved. For applied loads less than 1,000 lb on the cement scale and 4,000 lb on the aggregate scale, the scales shall be accurate to 2.0% or 1 gradation.

Meters for both admixtures and water shall be accurate to within 1.0%.

Means of control shall be provided so that as the quantity desired in the weighing hopper is approached, the materials may be added at a slower rate and shut off with precision. The following proportioning tolerances shall be used for batching:

- | | |
|----|--|
| 30 | <ol style="list-style-type: none"> 1. admixtures.....±3% 2. aggregates.....±2% 3. cementitious materials.....±1% 4. water, volume or weight.....±1%. |
|----|--|

The plant shall be equipped with a recording device capable of producing a ticket to permanently record the batch number, time of day, weight of all materials in the mix, volume or weight of mixing water added, and admixture quantities or equipped with a suitable non-resettable batch counter which will indicate correctly the number of batches produced. The CMD number shall be included on the ticket.

40 **(c) Material Storage**

The plant shall have separate storage bins or tanks for each material in the mixture. Each compartment shall discharge efficiently and freely into the weighing hopper or feed through a meter.

1. Aggregates

The aggregate storage area shall be well drained. All stockpiles shall be sufficiently separated and identified by signs or other approved methods.

2. Cementitious Materials

- 50 The storage bins shall be sealed and vented to preclude dusting during operation and have a sampling port.

3. Admixtures

Separate tanks for each admixture shall be provided.

(d) Hoppers

- 60 Weighing hoppers shall be constructed to eliminate accumulation of materials and to discharge fully. The fine aggregate and coarse aggregate shall be weighed separately into a weigh hopper in the respective amounts defined in the CMD. Separate scales and hoppers shall be used for weighing the cement. Pozzolans may be weighed into the cement hopper in one cumulative operation provided that the portland cement is weighed in first.

(e) Mixing System

The concrete mixing system shall be either a central stationary mixer or a transit truck mixer. Each mixer shall have attached in a prominent place a manufacturer's plate showing the capacity of the drum in terms of volume of mixed concrete, the

speed of rotation of the mixing drum or blades, and the manufacturer's name and address.

70

The mixer shall be capable of combining the ingredients of the concrete within the specified time into a thoroughly mixed and uniform mass.

1. Central or Stationary Mixers

Stationary mixers shall be equipped with a timing device which does not enable the batch to be discharged until the specified mixing time has elapsed.

2. Truck Mixers

80

Truck mixers shall be equipped with means by which the number of revolutions of the drum at mixing speed may be verified.

508.03 Transportation

(a) Truck Mixers and Truck Agitators

Truck mixers and agitators shall be capable of maintaining and discharging the concrete at a satisfactory rate and degree of uniformity. The haul units shall be examined daily for accumulations of hardened concrete or mortar and compared to the manufacturer's standard for wear of blades.

90

(b) Non-Agitator Trucks

Bodies of non-agitating hauling equipment shall be smooth, mortar tight, metal containers. They shall be capable of discharging the concrete at a controlled rate. The bodies shall be examined daily for accumulations of hardened concrete, mortar, or foreign matter.

508.04 Placement Equipment

(a) Slipform

100

The paver shall spread, consolidate, and shape the freshly placed concrete in one complete pass to provide a dense and homogeneous pavement. The paver shall be of sufficient weight and power to construct the specified PCCP, at an adequate variable forward speed, and without transverse, longitudinal, or vertical instability. The paver shall be equipped with an automated steering and elevation control system.

110

The paver shall consolidate by vibrating the concrete for the full width and depth of the PCCP. Vibration shall be accomplished by internal vibrators, which have a variable frequency range of 7,000 to 12,000 vibrations per minute. The amplitude of vibration shall be between 0.025 in. and 0.06 in. The vibrators shall be spaced and operated to achieve acceptable consolidation. The paver shall include a handheld tachometer or other suitable device for measuring the frequency of the vibrators. The automated vibrator control shall be capable of stopping vibration when forward movement ceases.

Mechanical tie bar inserters shall be rigidly attached to the paver and may be operated manually or automatically controlled.

A mechanical belt placer, if used, shall have a re-combining deflector plate mounted on the end of the discharge belt.

120 **(b) Form Riding Equipment**

The finishing machine shall be supported by forms and be equipped with two or more oscillating type transverse screeds and a transverse smoothing float.

130 Forms for riding equipment shall be of sufficient thickness to maintain the true cross section and shall be furnished in sections no less than 10 ft in length. Forms shall have a minimum depth equal to the prescribed edge thickness of the concrete pavement without a horizontal joint, and a minimum base width equal to the depth of the forms. Flexible or curved forms shall be of an acceptable design. Forms shall be provided with adequate devices for secure setting so that when in place they can withstand, without visible spring or settlement, the impact and vibration of the consolidating and finishing equipment. Flange braces shall extend outward on the base a minimum of 2/3 of the height of the form. The top face of the form shall not vary from a true plane by more than 1/8 in. in 10 ft and the upstanding leg shall not vary by more than 1/4 in. The forms shall contain provisions for locking the ends of abutting form sections together tightly for secure setting.

140 The transverse screed and transverse smoothing float shall be suspended from and guided by a rigid frame. The frame shall have a maximum effective wheel base of 14 ft. The length of the float shall be approximately 2 in. less than the normal width of the pavement and have an adjustable crown section. The forward speed of the float shall be adjustable.

150 The vibration equipment shall consolidate the full width and depth of the strip of PCCP being placed. Vibrators may be either the surface pan type or the internal type with either immerse tube or multiple spuds. Vibrators may be attached to the spreader or the finishing machine or mounted on a separate carriage. The frequency of the surface pan type shall be 3,500 impulses per minute or greater. The frequency of the internal type shall have no less than 5,000 impulses per minute for tube vibrators and spud vibrators shall have a frequency of from 10,000 to 12,000 impulses per minute in air. The paver shall include a device, such as a handheld tachometer for measuring the frequency of the vibrators. Vibrators shall have automatic controls, which stop vibration when forward motion ceases. The maximum spacing of spud vibrators shall be 2 ft. A warning device shall be connected to each vibrator circuit to indicate a failure of any individual vibrator and shall be visible from the ground.

(c) Hand Placement

1. Steel Forms

Steel forms shall be 10 ft or greater in length. Forms shall be capable of being

160 staked in three locations or more for each 10 ft section and shall be equipped to interlock. Forms shall support finishing equipment without deflection in either the vertical or horizontal direction. The top face of the form shall not vary from a true plane by more than 1/8 in. in 10 ft.

2. Wood Forms

Wood forms shall support finish equipment without deflection in either vertical or horizontal direction.

3. Finishing Equipment

170 The finish device or machine shall be capable of producing a uniform surface free of voids and in accordance with the planned profiles and cross section.

A mechanical tube finisher shall consist of a single or multiple rotating strike-off/finish tubes setting approximately transverse to the longitudinal movement of the machine. The length of finish tubes shall be a minimum of 2 ft longer than the planned PCCP width. The forward speed of the machine as well as the rate of the finish tube rotation shall be variable and it shall be reversible to allow for multiple finish passes.

180 A vibratory screed finisher shall consist of a truss frame with a minimum base width of 1 ft, which extends across the transverse width of the PCCP. The frame shall extend 2 ft beyond the width of the PCCP and shall hold its shape when moved forward. The screed shall move forward with either hydraulic or manual wenchers, which are capable of maintaining the screed at a right angle to the direction of travel. The screed shall be vibrated as it moves forward and the vibration shall stop when forward motion ceases. Vibration shall be accomplished with mechanical driven eccentric weights or with auxiliary driven pneumatic vibrators.

190 A mechanical bridge deck finishing machine shall consist of a single or multiple rotating cylinders setting approximately parallel to the longitudinal movement of the machine and operating transversely. The forward motion of the machine as well as the transverse movement of the finish cylinders shall be variable.

A hand operated strike off shall be rigid and shall hold its shape when moved forward with a combined longitudinal and transverse motion.

A mechanical belt placer, if used, shall have a re-combining deflector plate mounted on the end of the discharge belt.

200 **4. Vibrators**

Hand spud vibrators shall be capable of transmitting 7,000 to 10,800 impulses per minute in air. The diameter of the head shall be 1 1/4 to 2 1/2 in.

508.05 Curing

Mechanical equipment shall be self-supported and ride on wheels or tracks located outside the paving lane. The mechanical sprayer shall be capable of applying a continuous uniform film at a minimum rate of 1 gal./150 sq ft and shall be of the fully atomizing type. The equipment shall provide adequate agitation of the compound during application.

210

Hand spraying equipment shall be of the fully atomizing type.

508.06 Texturing Equipment

Mechanical texturing equipment shall be capable of forming transverse grooves of uniform depth and alignment in the plastic PCCP, without tearing the surface. The texturing comb shall have steel tines spaced as specified.

220

Hand tools consisting of fluted floats, rakes with spring steel tines, or finned floats with a single row of fins shall produce grooves which conform to the same requirements as those specified for the grooves formed by the mechanical equipment.

508.07 Sawing Equipment

Sawing equipment shall be self-propelled single or gang-mounted units. The saw shall be capable of maintaining the specified alignment and depth of cut without damaging the PCCP.

508.08 Miscellaneous Equipment**(a) Hand Tools**

230

Long handled floats used to smooth and fill in open texture areas in the pavement shall have blades no less than 5 ft in length and 6 in. in width. Equipment made of or coated with aluminum or aluminum alloys shall not be used.

Straightedges shall be 10 ft in length and mounted on a long handle. The handle shall be 3 ft longer than 1/2 of the width of the pavement being placed.

(b) Joint Sealing

240

Joint sealant material shall be installed using manufacturer's recommended equipment.

Air compressors shall be capable of producing a minimum air pressure of 80 psi.

Water blasting equipment shall be capable of operating at 1,500 psi without damaging the PCCP.

(c) Grinding

Grinding shall be completed by mechanical grinding equipment using diamond tipped saw blades mounted on a power driven, self-propelled machine containing transverse and longitudinal grade controls. The cutting head shall be no less than 36 in.

250 wide to produce a uniform texture per the full width of the cutting head shaft. The pavement surface after cutting shall have a uniform texture but shall not be smooth or polished. Tearing or dislodging of aggregates will not be allowed.

508.09 Testing Facility and Equipment

(a) Testing Facility

260 Testing facility shall be capable of maintaining a controlled curing environment in accordance with AASHTO T 23 and contain sufficient storage tanks with curing solution to cure both production control and acceptance test beams. Water shall be conveniently available for cleaning testing equipment and for serving other tasks at the facility. Office space, having suitable heat and air conditioning, shall be provided to the Department within the testing facility. A telephone shall be provided in the testing facility. Floor space shall be provided for a Department furnished beam breaker.

A current set of AASHTO's Standard Specifications for Transportation Materials and Methods of Sampling and Testing, Part 2 Tests, and ASTM C 173 shall be provided.

270 (b) Testing Equipment

Testing equipment shall be provided to perform production control testing and shall be maintained in suitable working order. The equipment shall be in accordance with AASHTO requirements where applicable. The Contractor shall provide a spud vibrator with power source in suitable working order.

(c) Profilograph

The profilograph shall be in accordance with ITM 912.

(d) Straightedge – 16 ft

280 A 16 ft straightedge shall be a rigid beam mounted on two solid wheels on axles 16 ft apart. The straightedge has a mounted push bar to facilitate propelling the device along or across the pavement. Tolerance points are located at the 1/4, 1/2, and 3/4 points and may be composed of threaded bolts capable of being adjusted to the tolerance required.

(e) Straightedge – 10 ft

A 10 ft straightedge is the same as a 16 ft straightedge except that the wheels are mounted 10 ft apart. A handheld rigid beam may be substituted.

THIS PAGE INTENTIONALLY LEFT BLANK