

52-13(3)

November 2005



- * All Pavement, Including All Shoulders
- 1) 90 kg/m² HMA Surface 9.5 mm
- (2) 150 kg/m² HMA Intermediate 19.0 mm
- (3) 240 kg/m² Minimum HMA Base 25.0 mm
- ** (4) 250 kg/m² QC/QA-HMA Intermediate OG25.0 mm
 - 5) 240 kg/m² HMA Base 25.0 mm
 - 6 Subgrade Treatment
 - 7 Variable-Depth Compacted Aggregate, No. 53
 - 8 Pipe, Type 4, Circular, 150 mm
- * Open graded mixtures OG19.0 mm or OG25.0 mm should be QC/QA-HMA, 5, 76. For all other mixtures, see Section 52-9.02 to determine the appropriate HMA mixture designation.
- ** Where underdrains are not required, Intermediate OG25.0 mm mix should be replaced with HMA Base 25.0 mm, minimum 270 kg/m².




FULL DEPTH HMA PAVEMENT,

≥ 30 MILLION ESALs

Figure 52-13A

52-13(4)



* Mainline

- 90 kg/m² HMA Surface 9.5 mm
- 150 kg/m² HMA Intermediate 19.0 mm
- 240 kg/m² Minimum HMA Base 25.0 mm
- 165 kg/m² QC/QA-HMA Intermediate OG25.0 mm
 - 240 kg/m² HMA Base 25.0 mm
 - **Subgrade Treatment**
 - Pipe, Type 4, Circular, 150 mm


* Shoulders

- 90 kg/m² HMA Surface 9.5 mm
- 270 kg/m² HMA Base 25.0 mm
- (9) Compacted Aggregate, No. 53, Base
- (11) Variable-Depth Compacted Aggregate, No. 53

(Depth equals mainline HMA thickness minus 150 mm)

FULL DEPTH HMA PAVEMENT. 10 MILLION ≤ ESALs < 30 MILLION Figure 52-13B

- OG25.0 mm mix should be replaced with HMA Base 25.0 mm, 180 kg/m².




- * Mainline Pavement (Section With Shoulders)
- 1) 90 kg/m² HMA Surface 9.5 mm
- 2) 150 kg/m² HMA Intermediate 19.0 mm
- (3) 150 kg/m² Minimum HMA Base 19.0 mm
- ** (4) 140 kg/m² QC/QA-HMA Intermediate OG19.0 mm
 - 5 180 kg/m² QC/QA-HMA Base 19.0 mm
 - 6 Subgrade Treatment
 - 10 Pipe, Type 4, Circular, 150 mm
 - * Shoulders
 - 7) 90 kg/m² HMA Surface 9.5 mm
 - 8) 270 kg/m² HMA Base 25.0 mm
 - 9 Compacted Aggregate, No.53, Base (Depth equals mainline HMA thickness minus 150 mm)
 - (11) Variable-Depth Compacted Aggregate, No. 53

FULL DEPTH HMA PAVEMENT,

1 MILLION ≤ ESALs < 10 MILLION
Figure 52-13C

- * Open graded mixtures OG19.0 mm or OG25.0 mm should be QC/QA-HMA, 5, 76. For all other mixtures, see Section 52-9.02 to determine the appropriate HMA mixture designation.
- ** Where underdrains are not required, QC/QA-HMA Intermediate OG19.0 mm mix should be replaced with HMA Base 19.0 mm, 150 kg/m².


52-13(6)



- * Mainline (Section With Shoulders)
- 1) 90 kg/m² HMA Surface 9.5 mm
- (2) 150 kg/m² HMA Intermediate 19.0 mm
- ** 3 480 kg/m² HMA Base 25.0 mm
 - 4 Subgrade Treatment
 - * Shoulders
 - (5) 180 kg/m² HMA Surface 9.5 mm
 - 6 225 mm Compacted Aggregate, No. 53, Base
 Or 5 & 6 may be replaced by
 300 mm Minimum Compacted Aggregate, No. 53, Base
 - 7 Variable-Depth Compacted Aggregate, No. 53

- * Where underdrains are not required, see Figure 52-13C.
- ** See Section 52-9.02 to determine the appropriate HMA mixture designation.
- *** Earth may be substituted for compacted aggregate dependent on geometric requirements for the usable shoulder width outside the paved area.

FULL DEPTH HMA PAVEMENT, < 1 MILLION ESALs
Figure 52-13D



* Mainline (Section With Shoulders)

- 1) 90 kg/m² HMA Surface 9.5 mm
- (2) 150-330 kg/m² HMA Intermediate 19.0 mm
- 3 125-200 mm Compacted Aggregate Base
 - 1 + 2 + 3 ≥ 300 mm
- (4) Subgrade Treatment


- * See Section 52-9.02 to determine the appropriate HMA mixture designation.
- ** Earth may be substituted for compacted aggregate dependent on geometric requirements for the usable shoulder width outside the paved area.


** Shoulders

- (5) 180 kg/m² HMA Surface 9.5 mm
- 6) 225 mm Compacted Aggregate, No. 53, Base
 Or 5 & 6 may be replaced by
 300 mm Minimum Compacted Aggregate, No. 53, Base
- 7 Variable-Depth Compacted Aggregate, No. 53

COMPOSITE HMA / COMPACTED AGGREGATE PAVEMENT < 1 MILLION ESALs

Figure 52-13E






Mainline and Shoulders

- 1 PCCP
- * (2) Subbase for PCCP (75 mm Coarse Aggregate No.8 On 150 mm Coarse Aggregate No.53, Base)
- (2A) 150 mm Compacted Aggregate, No. 53, Base
- (3) Variable-Depth Compacted Aggregate, No. 53
- 4 Pipe, Type 4, Circular, 150 mm
- 5 Subgrade Treatment
- (6) Longitudinal Joint or Longitudinal Construction Joint. See Figure 52-13R for Pavement Joint Options.
- 7 Concrete Median Barrier
 - * Where underdrains are not required, Dense Graded Subbase should be used.

PCCP SECTION WITH PCC SHOULDER, ≥ 30 MILLION ESALs Figure 52-13F



Mainline


- 1 PCCP
- *(2) Subbase for PCCP (75 mm Coarse Aggregate No.8 On 150 mm Coarse Aggregate No.53, Base)

Shoulders

- ** (3) 90 kg/m² HMA Surface 9.5 mm 180 kg/m² HMA Intermediate 19.0 mm
- ** (4) HMA Base 25.0 mm
 - 5 Compacted Aggregate, No. 53, Base
 - (6) Variable-Depth Compacted Aggregate, No. 53
 - 7 Subgrade Treatment
 - 8 Longitudinal Joint or Longitudinal Construction Joint
 - 9) Pipe, Type 4, Circular, 150 mm
 - * Where underdrains are not required, Dense Graded Subbase should be used.
 - ** See Section 52-9.02 to determine the appropriate HMA mixture designation.

Typical Pavement Sections

52-13(10)



Mainline


- (1) PCCP
- * 2 Subbase for PCCP (75 mm Coarse Aggregate #8 On 150 mm Coarse Aggregate #53, Base)
- (3) Longitudinal Joint or Longitudinal Construction Joint
- 4 Subgrade Treatment
- 5 Pipe, Type 4, Circular, 150 mm
- 6 See Figure 52-13Q for Geotextile Installation Requirements for Curbs (Required Only With Underdrains)
 - * Where underdrains are not required, Dense Graded Subbase should be used.
- (7) 150 mm Compacted Aggregate, No. 53, Base

Typical Pavement Sections

* Open graded mixture OG19.0 mm should be QC/QA-HMA, 5, 76. For all other mixtures, see Section 52-9.02 to determine

the appropriate HMA mixture designation.


November 2005



* Shoulder Tangent Section

- 90 kg/m² HMA Surface 9.5 mm on Variable HMA Intermediate 19.0 mm
- Compacted Aggregate, No. 53
- Pipe, Type 4, Circular, 100 mm
- * Mainline Superelevated Section
- 90 kg/m² HMA Surface 9.5 mm
- 120 kg/m² HMA Intermediate 12.5 mm
- Variable (110 kg/m² Min.) QC/QA-HMA Intermediate OG19.0 mm to attain proper superelevation
- Do not mill Existing PCCP if superelevated

OVERLAY (TILT TO CROWN SECTION) Figure 52-13 I



* Mainline


90 kg/m² HMA Surface 9.5 mm 120 kg/m² HMA Intermediate 12.5 mm Variable depth QC/QA-HMA, 5, 76, Intermediate OG19.0 mm (110 kg/m² at Pavement Edge, 150 kg/m² at €)

* Shoulder

Typical Pavement Sections

- (2) 90 kg/m² HMA Surface 9.5 mm on 240 kg/m² HMA Base 25.0 mm
- Compacted Aggregate, No. 53
- Pipe, Type 4, Circular, 100 mm. See Figure 52-13K for Retrofit Underdrain Detail.
 - * Open graded mixture OG19.0 mm should be QC/QA-HMA, 5, 76. For all other mixtures, see Section 52-9.02 to determine the appropriate HMA mixture designation.

OVERLAY (CROWN TO CROWN SECTION) FIGURE 52-13J




Notes:

- Open graded mixture OG19.0 mm should be QC/QA-HMA,
 76. For all other mixtures, see Section 52-9.02 to determine the appropriate HMA mixture designation.
- 2. Median installation shown. Outside installation reversed as appropriate. However, slope break point is required.

RETROFIT UNDERDRAIN


Figure 52-13K



- 1) Dimension x is 0.6 m min., 1.2 m max. See Fig. 45-1A(1).
- 2 Where a HMA Base 25.0 mm course is used, the geotextile fabric shall extend under the course.
- 3. Median Installation shown. •utside Installation Reversed as Applicable.

All dimensions are in mm unless otherwise noted


UNDERDRAIN FOR HMA PAVEMENT ≥ 30 MILLION ESALs Figure 52-13L



- 1) Where a HMA Base 25.0 mm course is used, the geotextile fabric shall extend under the course.
- 2. Median Installation shown. Outside Installation Reversed as Applicable.

UNDERDRAIN FOR HMA PAVEMENT ≥ 30 MILLION ESALs Figure 52-13M


All dimensions are in mm unless otherwise noted



CONCRETE CURB AND GUTTER SECTION FOR HMA PAVEMENT WITH UNDERDRAIN

Figure 52-13N

All dimensions are in mm unless otherwise noted




Note: See Section 52-9.02 to determine the appropriate HMA mixture designation.

CONCRETE CURB AND GUTTER SECTION FOR HMA PAVEMENT WITHOUT UNDERDRAIN


Figure 52-13 O

All dimensions are in mm unless otherwise noted



PCCP WITH UNDERDRAIN

Figure 52-13P




CURBED PCCP WITH UNDERDRAIN

Figure 52-13Q

Note: Option to be determined by the contractor.

OPTIONS A AND B:




OPTION C:

Longitudinal Joint or

Longitudinal Constr. Joint

Type D-1 Contraction Joint


Option B: Longitudinal Constr. Joint



MEDIAN EDGE OF CONCRETE PAVEMENT LONGITUDINAL JOINT OPTIONS

Figure 52-13R

* Open graded mixtures OG19.0 mm or OG25.0 mm should be QC/QA-HMA, 5, 76. For all other mixtures, see Section 52-9.02 to determine the appropriate HMA mixture designation.




*Ramp

- 1) 90 kg/m² HMA Surface 9.5 mm
- 2) 150 kg/m² HMA Intermediate 19.0 mm
- 3) 180 kg/m² Minimum HMA Base 19.0 mm or HMA Intermediate 19.0 mm
- (4) 140 kg/m² QC/QA-HMA Inteermediate OG19.0 mm
- 5) 180 kg/m² QC/QA-HMA Base 19.0 mm or HMA Intermediate 19.0 mm
- 6 Subgrade Treatment
- 7) Variable-Depth Compacted Aggregate, No. 53
- 8) Pipe, Type 4, Circular, 150 mm

FULL-DEPTH HMA RAMP Figure 52-13S

Part V - Road Design



Ramp

- 1 PCCP
- 2 Subbase for PCCP (75 mm Coarse Aggregate, No. 8 on 150 mm Coarse Aggregate, No. 53, Base)
- Variable Depth Compacted Aggregate, No. 53
- Subgrade Treatment
- (5) Pipe, Type 4, Circular, 150 mm

PCCP RAMP


Figure 52-13T

52-13(23)

November 2005

Note:

Open graded mixture OG19.0 mm should be QC/QA-HMA, 5, 76. For all other mixtures, see Section 52-9.02 to determine the appropriate HMA mixture designation.



Ramp

1 90 kg/m² HMA Surface 9.5 mm on 120 kg/m² HMA Intermediate 12.5 mm on 120 kg/m² QC/QA-HMA, 5, 76, Intermediate OG19.0 mm

Shoulder

- 2 90 kg/m² HMA Surface 9.5 mm on 240 kg/m² HMA Base 25.0 mm
- (3) Variable-Depth Compacted Aggregate, No. 53
- 4 Pipe, Type 4, Circular, 100 mm (See Figure 52-13K for Retrofit Underdrain Detail)

RAMP WITH OVERLAY


Figure 52-13U

Typical Pavement Sections

52-13(24)

Notes:

- Open graded mixtures OG 19.0 mm or OG 25.0 mm should be QC/QA-HMA, 5, 76. For all other mixtures, see Section 52-9.02 to determine the appropriate HMA mixture designation.
- Concrete Curb and Gutter desirable.
 Type B curb may be used where drainage is away from it.




HMA PAVEMENT WITH CONCRETE CURB AND UNDERDRAIN Figure 52-13V

52-13(25)

November 2005

Notes:

See Section 52-9.02 to determine the appropriate HMA mixture designation.



HMA PAVEMENT WITH CONCRETE CURB AND NO UNDERDRAIN Figure 52-13W

Light-Duty HMA / Aggregate Composite Section (Equivalent to Class II Drive Section):

90 kg/m² HMA Surface Type A on 150 kg/m² Intermediate Type A on 200 mm Min. Compacted Aggregate Base, No. 53

Medium-Duty HMA / Aggregate Composite Section (Equivalent to Class IV Drive Section):

90 kg/m² HMA Surface Type B on 150 kg/m² Intermediate Type B on 200 mm Min. Compacted Aggregate Base, No. 53

Heavy-Duty HMA / Aggregate Composite Section (Equivalent to Class VI Drive Section):

90 kg/m² HMA Surface Type B on 330 kg/m² Intermediate Type B on 250 mm Min. Compacted Aggregate Base, No. 53

PCCP Section:

150 mm Min. PCCP for Approaches on 150 mm Dense Grade Subbase

PARKING LOT PAVEMENT SECTIONS

Figure 52-13X