

619-B-181 PAINTING BRIDGE STEEL

(Adopted 05-18-09)

The Standard Specifications are revised as follows:

SECTION 619, BEGIN LINE 161, DELETE AND INSERT AS FOLLOWS:

On existing bridges with hazardous-based coatings, either steel grit blasting abrasives in accordance with SSPC AB 43 shall be used and recycled or mineral/slag blasting abrasives in accordance with SSPC AB 31 shall be used and the waste residue generated shall be treated at a facility rendering it to a non-hazardous state and disposed of in accordance with all applicable Federal, State, and local regulations. If steel grit blasting abrasives are used, the recycling equipment shall be capable of separating the blasting abrasive from the paint debris.
