

406-R-676 TACK COAT

(Adopted 03-15-18)

The Standard Specifications are revised as follows:

SECTION 406, BEGIN LINE 21, DELETE AND INSERT AS FOLLOWS:

406.04 Preparation of Surface

The existing surface to be treated shall be free of foreign materials deemed detrimental by the Engineer. *The surface to which the asphalt material is applied shall not have standing water and shall be cleaned of dust, debris and any substances that will prevent adherence.*

406.05 Application of Asphalt Material

The asphalt material shall be ~~uniformly~~ applied at the rate of from 0.05 to 0.10 gal./sq yd, or as otherwise specified or directed. *The asphalt material shall be uniformly applied across the entire width of pavement to be overlaid and shall cover a minimum of 95% of the surface. Areas of inadequate coverage that create streaking or areas of excessive coverage that create ponding shall be corrected to obtain an even distribution.*

~~Tack coat shall not be applied to a wet surface. The rate of application, temperature, and areas to be treated shall be approved prior to application. Excessive tack coat shall be corrected to obtain an even distribution.~~
