

## 704-B-308 CONCRETE FLOOR SLABS CURING

*(Adopted 07-19-18)*

The Standard Specifications are revised as follows:

SECTION 704, BEGIN LINE 146, DELETE AND INSERT AS FOLLOWS:

**704.06 Curing**

Floor slabs shall be cured in accordance with ~~one of the methods of 702.22(a)1. If membrane curing is used, no exposed reinforcement shall be coated with the material.~~ Where it has been determined that a surface treatment to prevent scaling is to be used, the Engineer may prohibit the use of the membrane forming curing compound on ~~the floor slab or~~ any part of the superstructure. All vertical surfaces with exposed reinforcement shall be cured in accordance with 702.22. The floor shall be protected from pedestrian and vehicular traffic. If walking is necessary, the surface shall be timber laid on a double burlap cushion or approved equivalent.

---