

302-R-689 SUBBASE

(Adopted 06-20-19)

The Standard Specifications are revised as follows:

SECTION 302, BEGIN LINE 32, DELETE AND INSERT AS FOLLOWS:

302.05 Spreading

The moisture content of the aggregate shall be between 4% and the optimum moisture content prior to placement when the aggregate is delivered to the project. Unless otherwise directed, water shall not be added to the aggregate on the grade. The aggregate shall be spread in uniform lifts with a spreading and leveling device approved by the Engineer. The spreading and leveling device shall be capable of placing aggregate to the depth, width, and slope specified. The compacted depth of each lift shall be a minimum of 3 in. and a maximum of 6 in. The aggregate shall be handled and transported to minimize segregation and the loss of moisture. In areas inaccessible to mechanical equipment, approved hand spreading methods may be used.

The moisture content of the aggregate shall be between 4% and the optimum moisture content when the aggregate is delivered to the project. Water shall not be added to the aggregate on the grade.
